



GROUND FLOOR
NOT TO SCALE

FIRST FLOOR
NOT TO SCALE

SECOND FLOOR
NOT TO SCALE

THIRD FLOOR
NOT TO SCALE



CORRIDORS TO BE REPAIRED

1. Wire brush the exposed and corroded reinforcement bars and coat with a Zinc based anti corrosive paint
2. 25mm thick screed to be laid over the existing screed by using an approved bonding agent after chipping the damaged existing screed (Newly laid screed should be lower than classroom floor finished level)
3. Finish the floor with an epoxy floor paint

AMMENDMENTS		
Issue	Date	Description