



**GREEN SYNTHESIS OF GOLD NANOPARTICLES USING AQUEOUS EXTRACT OF
BAUHINIA PURPUREA**

¹*A. Meena and ²R. Senthilraj

¹Dhanalakshmi Srinivasan College of Pharmacy, Perambalur-621212.

²Dr.M.G.R Educational and Research Institute, Velappanchavadi, Chennai -77.



*Corresponding Author: A. Meena

Dhanalakshmi Srinivasan College of Pharmacy, Perambalur-621212.

Article Received on 22/03/2024

Article Revised on 11/04/2024

Article Accepted on 03/05/2024

ABSTRACT

The synthesis of gold nanoparticles (Au-NPs) is performed by the reduction of aqueous gold metal ions in contact with the aqueous extract of plant, *Bauhinia Purpurea* (*B.Purpurea*). An absorption peak of the gold nanoparticles is observed at the range of 540–550 nm using UV-visible spectroscopy. All the diffraction peaks at $2\theta = 38.01^\circ$, 44.26° , 64.53° , and 77.49° that index to (100), (37), (29), and (44) planes confirm the successful synthesis of Au-NPs. Mostly spherical shape particles with size range of 32.96 ± 5.25 nm are measured using transmission electron microscopy (TEM). From the FTIR results, the peaks obtained are closely related to phenols, flavonoids, benzophenones, and anthocyanins which suggest that they may act as the reducing agent. This method is environmentally safe without the usage of synthetic materials which is highly potential in biomedical applications.

KEYWORDS: An absorption peak of the gold nanoparticles is observed at the range of 540–550 nm using UV-visible spectroscopy.

1. INTRODUCTION

Nanotechnology is technology that deals with nanoscale materials range from 1 to 100 nm and their applications. Among different type of nanomaterials, noble metal nanoparticles gained considerable attention due to their special catalytic, electronic, and optical properties. Gold nanoparticles (Au-NPs) have been widely investigated due to their uniqueness especially in biomedication. The multiple surface functionality of Au-NPs ease nanobiological attachment of Au-NPs with drug, oligonucleotides, antibodies, and protein. The optical property of Au-NPs also enables them to play a role in bioimaging by acting as marking agent.

Despite the popularity and development of synthesizing nanoparticles using chemical and physical methods, the need to establish environmental friendly methods that do not involve the usage of toxic chemicals is crucial especially in medical purpose. Synthesis method that uses natural products as reducing agents need more focus to reduce the hazards on environment and human. Greener substrates such as enzyme, fungus, and algae were reported successfully in the production of Au-NPs. However, as compared to the difficulties faced in microbe assisted synthesis, plant mediated synthesis is developing due to the ease to handle and to control the size and shape of nanoparticles. Plant-based synthesis is relatively fast, safe, and light and works under room

condition without the need of high physical requirement. Every part of the plant is proved to be useful especially the leaves, but few reports are targeted on the Plant.

Bauhinia Purpurea (*B.Purpurea*) which is commonly belong to the family of fabaceae. It can grow up to 5.2 m in height and is mainly cultivated in the United States of America, Hawaii, Coastal California, Southern Texas, Southwest Florida. Traditionally, Southeast has been used as medicine to treating swelling, bruises, boils, and ulcers. Secondary metabolites such as phenolic acid, flavonoids, alkaloids, and terpenoids that are contained in plant crude extract are involved in the reduction of nanoparticles.

Bauhinia Purpurea including 5,6-dihydroxy-7-methoxyflavone 6-O- β -D-xylopyranoside, bis [3',4'-dihydroxy-6-methoxy-7,8-furano-5',6'-monomethylalloxy]-5-C-5-biflavonyl and (4'-hydroxy-7-methyl 3-C- α -L-rhamnopyranosyl)-5-C-5-(4'-hydroxy-7-methyl-3-C- α -D-glucopyranosyl) bioflavonoid, bibnzyls, dibenzoxepins, mixture of phytol fatty esters, Lutein, Beta sitosterol, isoquercitin and astragalins. antioxidant, antitumour, antiallergic, and antiviral properties where there are researches that shows that have high potential antioxidants which are believed to take part in the synthesis reaction of Au-NPs. Also, different kind of flavonoids, benzophenones, and anthocyanins present in

the plant may be involved closely in the reduction of nanoparticles.

To the best of our knowledge, there is no work reported on adopting *B. Purpurea* in the synthesis of Au-NPs or any other metal nanoparticles. Here, we demonstrate the biosynthesis and characterization of Au-NPs by using tetra-chloroaurate and aqueous extract of *B. Purpurea*.

2. Methods

2.1. Chemicals. *B. Purpurea* were collected from Xavier Research foundation, Palayamkottai, Tamilnadu. Analytical grade tetrachloroaurate salt (HAuCl_4 , 99.98%)



Figure 1: Photos of the Colour Changes after the Addition of Tetrachloroaurate Where (a) is the bauhinia purpurea, (b) pure plant extract, and (c) au-nps solution after the reaction with dilution.

Synthesis of Au-NPs. In a conical flask, 20 mL of the peel extract was reacted with 10 mM of tetrachloroaurate at room temperature under static conditions. The colour change of the reaction was observed and the time taken for the changes was noted. The solution colour changes immediately from pale brownish to purple colour indicating the formation of [Au/G.mangostana]. The Au-NPs nanoparticles emulsion obtained was kept at 4°C.


2.4. Characterization of Au-NPs. The reduction of Au-NPs was confirmed by using UV-vis spectroscopy at regular intervals in the range of 300 to 1000 nm (Shimadzu, UV-1800 UV-VIS Spectrometer). The nanoparticles emulsion was oven dried at 40°C for one day. The dried sample was collected and examined for the structure and composition using powder X-ray diffraction spectroscopy. The data was recorded using PANalyticXpert Pro ($\lambda = 0.15406$ nm) at 45 kV and 20 mA. The dried sample was scanned in the range of $2\theta = 10-80^\circ$ with $2^\circ/\text{min}$. Transmission electron microscopy (TECNAI, G2 F20) was used to investigate the size and morphology of the Au-NPs using SC1000 Orius CCD camera. The stability of Au-NPs was measured using Particulate Systems Nano-Plus Zeta/Nano Particle Analyser, Japan. The bioreduction compounds that are responsible for the reaction were determined using Fourier Transform Infrared spectroscopy. The spectrum was obtained by Thermo Scientific Nicolet 6700 system with 16 scans per sample at the range of 550–4000 cm^{-1} .

was purchased from Sigma-Aldrich, Mumbai and used as gold precursor. All reagents used were of analytical grade. All aqueous solutions were prepared using distilled water. All glassware used was cleaned and washed with distilled water and dried before used.

Preparation of Aqueous *B. Purpurea* Extract. The plants were thoroughly remove dirt and dried in sun brownish to purple colour indicating the formation of [Au/*B. Purpurea*]. The Au-NPs nanoparticles emulsion obtained was kept at 4°C.

3. RESULTS AND DISCUSSION

B. Purpurea extract (0.50 g, 20 mL) acts as both the reducing and stabilizing agent and HAuCl_4 (10 mM) acts as the gold precursor. The reduction of HAuCl_4 was indicated by the colour changes of *B. Purpurea* extract as shown in Figure 1. The reaction was rapid as the pale brownish colour of the *B. Purpurea* extract turns into dark brown colour within 3 min indicating formation of Au-NPs. The possible chemical equations for synthesizing the Au-NPs are



After dispersion of HAuCl_4 in the *B. Purpurea* aqueous solution matrix, the extract was reacted with the functional groups of *B. Purpurea* components to form [Au/ *B. Purpurea*].

3.1. UV-Visible Spectroscopy Study.

The presence of Au-NPs is confirmed by UV-vis spectra in Figure 2. The results showed that a sharp peak appears at the range of 540–550 nm. It is further confirmed by other characterizations that this peak indicates the formation of monodispersed spherical shape Au-NPs. The reaction takes place within 3 minutes with obvious colour change.




Figure 2: UV-vis Absorbance Bands For Au-NPs Forms Using B. Purpurea Extract.

3.2. X-Ray Diffraction Analysis.

Powder X-ray diffraction pattern in Figure 3 shows that the Au-NPs synthesized is in crystalline structure. The spectrum gives an intense peak at $2\theta = 38.01^\circ$, 44.26° and 64.53° which correspond to the (100), (37) and (30)




Figure 3: XRD spectra for Au-NPs forms using B. Purpurea extract and the intensity peak of the reference peak.

3.3. Transmission Electron Microscopy and Scanning Electron Microscopy Study.

The size and the morphology of the Au-NPs synthesized was investigated using the SEM which is represented by Figure 4. The Au-NPs is well dispersed with B. Purpurea matrix surrounding it indicating that B. Purpurea matrix acts as the capping agent to separate the Au-NPs from

plane proving the structure of Au-NPs to be face center cubic (fcc). The crystallinity of Au-NPs is pure by comparing its XRD pattern with the database. However, there is shifting of the peaks with database where crystal structure of pure metallic Au-NPs is present. The particle size of Au-NPs can be estimated using the Debye-Scherrer equation,

$$d = k\lambda / (\beta \cdot \cos \theta), (2)$$

Where d is the average crystallite size, k is the Scherrer constant (0.9), λ is the X-ray wavelength (0.154 nm), β is the line broadening in radians, and θ is the Bragg angle.^[31] By using the Scherrer equation, 16 nm is calculated to be the average crystallite size of the Au-NPs.

aggregation. The average size of the Au-NPs synthesized is 200 ± 5.25 nm with mostly.

3.3. spherical and some hexagonal and triangular shape. The average size of the Au-NPs synthesized is 132.96 ± 5.25 nm with mostly spherical and some hexagonal and triangular shape




Figure 4: SEM and TEM image of the Au-NPs forms using B. Purpurea extract of the particles size of Au-NPs.

3.4. Zeta Potential Study

The stability of Au-NPs was per-formed using zeta potential. A zeta value of ± 30 mV is needed for a suspension to be physically stable while ± 20 mV is necessary for a combined electrostatic and steric

condition. The zeta potential results for pure B. Purpurea extract are -14.68 mV, whereas the reading of Au-NPs formed using the extract reduced to -20.82 mV (Figure 5). Thus, Au-NPs formed show an acceptable stability with reading not less than the required stable expression.




Figure 5: Zeta Potential Image of Au-NPs Form by Using B. Purpurea Extract.

3.5. Fourier Transform Infrared Spectroscopy Study

FTIR spectroscopy was carried out to determine the potential functional groups that are responsible for the reduction of Au-NPs. Figure 6 shows the spectra obtained from pure B. Purpurea extract and Au-NPs synthesized using the B. Purpurea extract. The major stretching appearing at $3000\text{--}3500$ cm^{-1} indicates the presence of O-H stretch which signifies the presence of phenols, flavonoids, benzophenones and anthocyanins. A little shifting occurs here, suggesting that the carbonyl group in the extract capped and stabilized the Au-NPs. Aside the O-H stretching, at the region of 2919 cm^{-1} and 2914 cm^{-1} the presence of C-H bond in xanthone and other compounds in the extract is significant. Bands

of C-H bond from B. Purpurea extract split into two, 2914 cm^{-1} and 2845 cm^{-1} , suggest that, after the formation of Au-NPs, the transmittance changed, while at the region of 1700 cm^{-1} it shows the presence of C=O stretching. At the region of $1600\text{--}1500$ cm^{-1} , C-C in ring aromatic bond also suggests the presence of aromatics structure exists in the B. Purpurea extract. The C-C aromatics stretch is observed for both spectra at the region of $1500\text{--}1400$ cm^{-1} which is relevant to the aromatic backbone that can be found mainly in the pericarp of B. Purpurea. Finally, C-O-C stretch can be found in the range of $1300\text{--}1000$ cm^{-1} where shifting occurs from 1279 cm^{-1} to 1234 cm^{-1} after capping with Au-NPs.




Figure 6: FT-IR graphs of Au-NPs form by using B. Purpurea extract.

4. CONCLUSION

This study gives an environmental favourable approach of the synthesis of Au-NPs using B. Purpurea extract. The extract demonstrates that the properties of both reducing and stabilizing agent owe to the presence of different compounds in B. Purpurea. The usage of extract from the plant takes full advantage which is economically friendly, efficient, and safe. No study is established before with the usage of B. Purpurea for the production of Au-NPs. The synthesized Au-NPs are potential to be applied in biomedical and other applications where nontoxicity is crucial.

REFERENCES

1. M. Zargar, A. A. Hamid, F. A. Bakar et al., "Green synthesis and antibacterial effect of silver nanoparticles using Vitex negundo L.," *Molecules*, 2011; 16(8): 6667–6676.
2. K. J. Rao and S. Paria, "Aegle marmelos leaf extract and plant surfactants mediated green synthesis of Au and Ag nanoparticles by optimizing process parameters using taguchi method," *ACS Sustainable Chemistry and Engineering*, 2015; 3(3): 483–491.
3. G. F. Paciotti, L. Myer, D. Weinreich et al., "Colloidal gold: a novel nanoparticle vector for

- tumor directed drug delivery,” *Drug Delivery*, 2004; 11(3): 169–183.
4. M. B. Mohamed, N. T. Adbel-Ghani, O. M. El-Borady, and M. A. El-Sayed, “5-Fluorouracil induces plasmonic coupling in gold nanospheres: new generation of chemotherapeutic agents,” *Journal of Nanomedicine and Nanotechnology*, 2012; 3(7): 1–7.
 5. D. A. Giljohann, D. S. Seferos, P. C. Patel, J. E. Millstone, N. L. Rosi, and C. A. Mirkin, “Oligonucleotide loading determines cellular uptake of DNA-modified gold nanoparticles,” *Nano Letters*, 2007; 7(12): 3818–3821.
 6. M. Ahmed, D. W. Pan, and M. E. Davis, “Lack of in vivo anti-body dependent cellular cytotoxicity with antibody containing gold nanoparticles,” *Bioconjugate Chemistry*, 2015; 26(5): 812–816.
 7. X. Geng and T. Z. Grove, “Repeat protein mediated synthesis of gold nanoparticles: effect of protein shape on the morphological and optical properties,” *RSC Advances*, 2015; 5(3): 2062–2069.
 8. K.-T. Yong, M. T. Swihart, H. Ding, and P. N. Prasad, “Preparation of gold nanoparticles and their applications in anisotropic nanoparticle synthesis and bioimaging,” *Plasmonics*, 2009; 4(2): 79–93.
 9. P. Kuppusamy, M. M. Yusoff, S. J. A. Ichwan, N. R. Parine, G.P. Maniam, and N. Govindan, “*Commelina nudiflora* L. edible weed as a novel source for gold nanoparticles synthesis and studies on different physical-chemical and biological properties,” *Journal of Industrial and Engineering Chemistry*, 2015; 27: 59–67.
 10. K. B. Narayanan and N. Sakthivel, “Facile green synthesis of gold nanostructures by NADPH-dependent enzyme from the extract of *Sclerotium rolfssii*,” *Colloids and Surfaces A: Physico-chemical and Engineering Aspects*, 2011; 380(1-3): 156–161.
 11. N. N. Dhanasekar, G. R. Rahul, K. B. Narayanan, G. Raman, and N. Sakthivel, “Green chemistry approach for the synthesis of gold nanoparticles using the fungus *Alternaria* sp,” *Journal of Microbiology and Biotechnology*, 2015; 25(7): 1129–1135.
 12. B. E. Naveena and S. Prakash, “Biological synthesis of gold nanoparticles using marine algae *Gracilaria corticata* and its application as a potent antimicrobial and antioxidant agent,” *Asian Journal of Pharmaceutical and Clinical Research*, 2013; 6(2): 179–182.
 13. H. Khanehzaei, M. B. Ahmad, K. Shamel, Z. Ajdari, M.A. Ghani, and K. Kalantari, “Effect of seaweed *Kappaphycus alvarezii* in the synthesis of Cu@Cu₂O core-shell nanoparticles prepared by chemical reduction method,” *Research on Chemical Intermediates*, 2015; 41(10): 7363–7376.
 14. X. Zhang, S. Yan, R. D. Tyagi, and R. Y. Surampalli, “Synthesis of nanoparticles by microorganisms and their application in enhancing microbiological reaction rates,” *Chemosphere*, 2011; 82(4): 489–494.
 15. I.-M. Chung, I. Park, K. Seung-Hyun, M. Thiruvengadam, and G. Rajakumar, “Plant-mediated synthesis of silver nanoparticles: their characteristic properties and therapeutic applications,” *Nanoscale Research Letters*, 2016; 11(1): 1–14.
 16. D. Philip, “Rapid green synthesis of spherical gold nanoparticles using *Mangifera indica* leaf,” *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 2010; 77(4): 807–810.
 17. S. S. Dash, B. G. Bag, and P. Hota, “*Lantana camara* Linn leaf extract mediated green synthesis of gold nanoparticles and study of its catalytic activity,” *Applied Nanoscience*, 2015; 5(3): 343–350.
 18. V. G. Kumar, S. D. Gokavarapu, A. Rajeswari et al., “Facile green synthesis of gold nanoparticles using leaf extract of antidiabetic potent *Cassia auriculata*,” *Colloids and Surfaces B: Biointerfaces*, 2011; 87(1): 159–163.
 19. B. Sadeghi, M. Mohammadzadeh, and B. Babakhani, “Green synthesis of gold nanoparticles using *Stevia rebaudiana* leaf extracts: characterization and their stability,” *Journal of Photochemistry and Photobiology B: Biology*, 2015; 148: 101–106.
 20. N. Yang, L. Weihong, and L. Hao, “Biosynthesis of Au nanoparticles using agricultural waste mango peel extract and its in-vitro cytotoxic effect on two normal cells,” *Materials Letters*, 2014; 134: 67–70.
 21. V. Ananth, M. Asad, N. Premkumar, S.M.D. Asday, and G.S. Rao, “Evaluation of wound healing potential of *Bauhinia Purpurea* leaf extracts in Rats” *Indian Journal of Pharmaceutical Sciences*, 2010; 72(1): 122–127.
 22. Bhawn Sunil Negi, Bharti P. Dave and Y.K. Agarwal, “Evaluation of Antimicrobial activity of *Bauhinia Purpurea* leaves under Invitro Conditions,” *Indian Journal of Microbiology*, 2012; 52(3): 360–365.
 23. S. Palwa, R. Mazumder, S. Bhattacharya, S. Kumari, A. Mazumder and D.P. Singh, “Pharmacognostical and Phytochemical evaluation of leaves of *Bauhinia Purpurea* Linn,” *Ancient Sciences*, 2010; 30(2): 28–32.
 24. Marimuthu Krishnaveni, “Antioxidant Potential of *Bauhinia Purpurea* leaf,” *International Journal of Pharmacy and Pharmaceutical Sciences*, 2014; 6(7): 558–560.
 25. Z.A. Zakaria, E.E. Abdul Hisam, M.S. Rofiee, M. Narhafizah, M.N. Somchit, L.K. Teh and M.Z. Salleh, “In vivo antiulcer activity of the aqueous extract of *Bauhinia Purpurea* leaf,” *Journal of Ethnopharmacology*, 2011; 137(2): 1047–1054.
 26. K. Anand, R. M. Gengan, A. Phulukdaree, and A. Chuturgoon, “Agroforestry waste *Moringa oleifera* petals mediated green synthesis of gold nanoparticles and their anti-cancer and catalytic activity,” *Journal of Industrial and Engineering Chemistry*, 2015; 21: 1105–1111.
 27. R. Vijayakumar, V. Devi, K. Adavallan, and D. Saranya, “Green synthesis and characterization of gold nanoparticles using extract of anti-tumor potent

- Crocus sativus,” *Physica E: Low-Dimensional Systems and Nanostructures*, 2011; 44(3): 665–671.
28. P. Kumar, P. Singh, K. Kumari, S. Mozumdar, and R. Chandra, “A green approach for the synthesis of gold nanotriangles using aqueous leaf extract of *Callistemon viminalis*,” *Materials Letters*, 2011; 65(4): 595–597.
 29. C. Coman, L. F. Leopold, O. D. Rugină et al., “Green synthesis of gold nanoparticles by *Allium sativum* extract and their assessment as SERS substrate,” *Journal of Nanoparticle Research*, 2014; 16(1): article 2158.
 30. J. Anuradha, T. Abbasi, and S. A. Abbasi, “An eco-friendly method of synthesizing gold nanoparticles using an otherwise worthless weed *Pistia stratiotes* L.,” *Journal of Advanced Research*, 2015; 6(5): 711–720.
 31. M. Mahdavi, F. Namvar, M. B. Ahmad, and R. Mohamad, “Green biosynthesis and characterization of magnetic iron oxide (Fe₃O₄) nanoparticles using seaweed (*Sargassum muticum*) aqueous extract,” *Molecules*, 2013; 18(5): 5954–5964.
 32. M. Faried, K. Shameli, M. Miyake et al., “Synthesis of silver nanoparticles via green method using ultrasound irradiation in seaweed *Kappaphycus alvarezii* media,” *Research on Chemical Intermediates*, 2016.
 33. P. P. Gan, S. H. Ng, Y. Huang, and S. F. Y. Li, “Green synthesis of gold nanoparticles using palm oil mill effluent (POME): a low-cost and eco-friendly viable approach,” *Bioresource Technology*, 2012; 113: 132–135.