



MICROENCAPSULATION OF PROBIOTIC: TECHNIQUES & BIOMATERIALS

Rajani Chauhan^{1*}, Vinod Singh², Seema Bisht Chauhan³

¹Department of Pharmaceutical Sciences, Banasthali University, Rajasthan.

²Department of Pharmaceutical Sciences, Gurukul Kangri university, Haridwar, Uttarakhand.

³Shri Guru Ram Rai Institute of Technology & Sciences, Dehradun.

Article Received on 25/01/2015

Article Revised on 14/02/2015

Article Accepted on 05/03/2015

***Correspondence for**

Author

Dr. Rajani Chauhan

Department of
Pharmaceutical Sciences,
Banasthali University,
Rajasthan.

ABSTRACT

The oral administration of most of the probiotics results in the lack of ability to survive in a high proportion of the harsh conditions of acidity and bile concentration commonly encountered in the gastrointestinal tract of humans. Providing Probiotic living cells with a physical barrier against adverse environmental conditions is therefore an approach currently receiving considerable interest. Probiotic encapsulation

technology has the potential to protect microorganisms and to deliver them into the gut. This review focuses mainly on the methodological approach of Probiotic encapsulation including biomaterials selection.

KEY WORDS: Probiotics, Biomaterials, Microencapsulation

INTRODUCTION

In recent years, increasing evidence indicating numerous health benefits associated with the intake of probiotic bacteria has created a big market of probiotic foods worldwide. The biggest challenge in the development of probiotic products is to maintain the adequate number of viable cells during the shelf life of the product as well as during the gastrointestinal (GI)-tract transit after consumption, so that the claimed health benefits can be delivered to the consumer.^[1,2,3,4] Consequently, there has been a growing interest in developing techniques to enhance the survival of probiotic bacteria particularly during the GI-tract transit of the cells.^[5,6,7,8]

Probiotic encapsulation technology is an exciting field of biopharmacy that has emerged and developed rapidly in the past decade. Based on this technology, a wide range of microorganisms have been immobilized within semi permeable and biocompatible materials that modulate the delivery of cells. The terms immobilization, entrapment and encapsulation have been used interchangeably in most reported literature.^[9]

To make a health claim, the therapeutic minimum level should be at least 10^7 cfu/g or ml of the product^[10], which can be achieved by using microencapsulation technology. Simultaneously, low level or poor survival of free probiotic bacteria was demonstrated by many studies.^[11]

Probiotics

Probiotics are defined as the living microorganisms administered in a sufficient number to survive in the intestinal ecosystem. They must have a positive effect on the host¹². The term 'probiotic' was first described by Lilly and Stillwell in 1965 as: "substances secreted by one microorganism that stimulate the growth of another". In 1974 Parker¹³ proposed that probiotics are "organisms and substances which contribute to intestinal microbial balance". In more modern definitions, the concept of an action on the gut microflora, and even that of live microorganisms disappeared. Salminen *et al.*^[14] defined probiotics as the 'food which contains live bacteria beneficial to health whereas Marteau *et al.*^[15] defined them as 'microbial cell preparations or components of microbial cells that have a beneficial effect on the health and well-being'. Some modern definitions include more precisely a preventive or therapeutic action of probiotics. Charteris *et al.* for example, defined probiotics as microorganisms which, when ingested, may have a positive effect in the prevention and treatment of a specific pathologic condition'. Finally, since probiotics have been found to be effective in the treatment of some gastrointestinal diseases^[15], they can be considered to be therapeutic agents. It is clear that a number of definitions of the term 'probiotic' have been used over the years but the one derived by the Food and Agriculture Organization of the United Nations/World Health Organization and endorsed by the International Scientific Association for Probiotics and Prebiotics^[16] best exemplifies the breadth and scope of probiotics as they are known today: 'live microorganisms which, when administered in adequate amounts, confer a health benefit on the host'

Table 1: Probiotics and their therapeutic applications

S.No	Probiotics strains	Therapeutic application
1	<i>L. rhamnosus</i> GG ^[17] , <i>S. boulardii</i> ^[18]	Antibiotic-Associated Diarrhea
3	<i>Bifidobacterium infantis</i> ^[19] <i>L. rhamnosus</i> GG ²⁰ , <i>B. longum</i> ^[21,22]	Inflammatory Bowel Syndrome ¹⁹
4	<i>L. rhamnosus</i> GG ²³	Atopic Dermatitis
5	<i>L. rhamnosus</i> GR-1 and <i>L. fermentum</i> RC-14 ^[24,25]	Genitourinary Disorders in Women
6	<i>Lactobacillus rhamnosus</i> GG ^[26]	Nonsteroidal anti-inflammatory Drug
7	<i>Lactobacillus fermentum</i> RC-14 ^[27]	Urinary tract infection
8	<i>Lactobacillus plantarum</i> 299v, ^[28]	Giardia infection
9	<i>B.coagulans</i> ^[29]	Rheumatoid arthritis
10	<i>Lactobacillus rhamnosus</i> GG, <i>Saccharomyces cerevisiae</i> ^[30,31]	Crohn's disease
11	<i>Lactobacillus rhamnosus</i> GG, <i>Lactobacillus acidophilus</i> , <i>Lactobacillus paracasei</i> , <i>Lactobacillus acidophilus</i> , and <i>Lactobacillus delbrueckii</i> ssp. <i>bulgaricus</i> strain LB-51 ^[32,33,34,35,36]	Prevention of colon cancer

Microencapsulation

Microencapsulation is described as a process of enclosing micron-sized particles of solids or droplets of liquids or gasses in an inert shell, which in turn isolates and protects them from the external environment. Microencapsulation has been developed approximately 40 years ago and widely used in the food industry due to its capabilities to provide good protection from moisture, heat or other extreme conditions which are undesirable factors for maintaining stability and viability of core materials.^[37]

Probiotics (usually 1-4 μm) are too big for nano-technology^[38], so microencapsulation is a useful tool for improving the delivery of the active probiotics.

The best application of probiotic encapsulation technology is the controlled and continuous delivery of cells in the gut. The potential benefit of this therapeutic strategy is to maintain greater cell viability despite the acidity into the stomach. In their viable state, probiotics may exert a health benefice on the host.^[17, 39]

Physicochemical properties of coating material affect the viability of encapsulated probiotic cells. Type and concentration of coating material, particle size, initial cell number, and bacterial strains are important during formulation.

Methods for Probiotic Microencapsulation

(a) Extrusion

Extrusion is the oldest & most common technique for converting hydrocolloids into microcapsules. The property of certain biopolymers such as alginate, carrageenan & pectin to form gel in presence of mineral such as calcium and potassium has been successfully applied to entrap probiotics using extrusion method. Bonding of multiple free carboxylic radicals by gelling ions leads to the formation of gels.^[38] (Champagne & Fustier 2007).

Extrusion involves projecting an emulsion core and coating material through a nozzle at high pressure. On a laboratory scale, this can be done by simple devices such as syringes are applied. If the droplet formation occurs in a controlled manner the technique is known as prilling.^[40] This is preferably done by pulsation of the jet or vibration of the nozzle.

In extrusion method Hydrocolloid solution was prepared & probiotics are added into the prepared solution to form cell suspension. These cells suspension is passed through the syringe needle to form droplets which are directly dripped into the hardening solution containing cations like calcium. When the droplets come in contact with hardening solution, alginate polymers surround the core to form a three dimensional lattice structure by cross-linking calcium ions.^[41]




Fig 1: Microencapsulation of Probiotics by Extrusion

(b) Emulsification

A small volume of the cell polymer suspension (i.e., the discontinuous phase) is added to a large volume of vegetable oil (i.e., the continuous phase). The mixture is then homogenized to form a water-in-oil emulsion. Once the water-in-oil emulsion is formed, the water-soluble polymer must be insolubilizing to form tiny gel particles within the oil phase. Microbeads produced by emulsion method are usually recovered by the membrane filtration technique. In contrary with the extrusion technique, it can be easily scaled up and the diameter of produced beads is considerably smaller (25 μm -2 mm). However, this method requires more cost for

performance compared with the extrusion method due to need of using vegetable oil for emulsion formation.^[41]




Fig 2: Microencapsulation of Probiotics by Emulsification

(c) Spray Drying

The process involves the dispersion of the core material into a polymer solution, forming an emulsion or dispersion, followed by homogenization of the liquid, then atomization of the mixture into the drying chamber.^[42] This leads to evaporation of the solvent (water) and hence the formation of matrix type micro capsules.

The advantage of the process is that it can be operated on a continuous basis. The disadvantage is that the high temperature used in the process may not be suitable for encapsulating probiotic bacterial cultures




Fig 3: Microencapsulation of Probiotics by Spray drying

(d) Freeze Drying

In this technique, the solvent is frozen and removed via sublimation.^[43] The techniques of spray-drying, freeze-drying or fluidized bed drying have shown their limitations because the cells encapsulated by these techniques are completely released into the product. Thereby, the cells are not protected towards the food matrix environment and in the presence of gastric fluid or bile.^[44] *Lactobacillus* F19 and *Bifidobacterium Bb12* cells were first encapsulated into enzymatically gelled sodium caseinate, and gel particles were freeze-dried to study the storage stability.^[45]

The process is performed by freezing probiotics in the presence of carrier material at low temperatures, followed by sublimation of the water under vacuum. Lyophilisation or freeze-drying is a very expensive technology, significantly more than spray-drying.^[46] However, most of freeze-drying process only provide stability upon storage and not or limited during consumption. Because of that, this technique is used as a second step of encapsulation process. The freeze-drying is useful to dry probiotics previously encapsulated by other different techniques, as emulsion^[45] or entrapment in gel microspheres. In this way it is possible to improve the stability in the gastrointestinal tract and optimize the beneficial effect of probiotic consumption.




Fig 4: Microencapsulation of Probiotics by Freeze drying

Selection of Biomaterials for Microencapsulation

(a) Pectin

Pectins are non-starch, linear polysaccharides extracted from the plant cell walls.^[47] It is major cell wall component in plants, playing a role in the control of cell growth & the defence against the invasion of microorganism. Pectin are composed of α -D-galacturonic acid, which are interrupted by single α -L- rhamnose residue. A difference between pectin is their content in methyl ester. High methoxy pectin forms gels due to hydrophobic interaction and hydrogen bonding between pectin molecules. Low methoxy pectin forms gel in the presence of di and polyvalent cations, which cross link and neutralize the negative charge of pectin molecule.^[48]




Fig 5: Chemical structure of Pectin

(b) Alginate

Alginate, is an anionic polysaccharide distributed widely in the cell walls of brown algae, where through binding with water it forms a viscous gum. In extracted form it absorbs water quickly; it is capable of absorbing 200-300 times its own weight in water.^[49] Chemically it is a linear polymer of heterogeneous structure composed of two monosaccharide units: acid α -L-guluronic (G) and acid β -D-mannuronic (M) linked by β (1–4) glycosidic bonds.^[50,51]

It is the most widely used hydrocolloid for microencapsulation of probiotics due to its gentle environment, low cost, simplicity, biocompatibility with the probiotics and properly resolve in the intestine to release encapsulated cells.^[52, 53,54]

Calcium alginate has been widely used for the encapsulation of lactic acid- and probiotic bacteria, mainly in the concentration range of 0.5-4% .^[55,56,57,58]

Alginate gels are insoluble in acidic media^[1, 59] usually alginate is used in concentration range of 0.5–4%.^[56]

Advantages of alginates are

- Easily form gel matrices around bacterial cells.
- They are not poisonous to the body (is safe or biocompatible).
- Alginates are cheap, mild process conditions (such as temperature) are needed for their performance.
- They can be easily prepared and performed (simplicity and ease of handling) and properly resolve in the intestine and release entrapped cells.
- Alginate gel matrix appropriately surrounds the bacterial cells with a diameter of 1-3 μm .

Dis advantages

- Susceptible to acidic environments, crackling and loss of mechanical stability in lactic acid.^[60]
- Fast diffusion of moisture and other fluid through the capsule which reduces their barrier properties against unfavorable environmental factor.^[54]
- Due to their high expenses, and a weak ability of scaling up as well as the formation of crackled and porous bead surfaces, which leads to fast diffusion of moisture and fluids through capsules which reduces their barrier properties against unfavorable environment factor, it is difficult in industrial scale applications.^[54]

These can be overcome by blending of alginate with another polymer like starch, coating other compound on its capsules.^[61, 62, 63]




Fig 6: Chemical Structure of Alginate monomer (a) and chain (b) conformations and a schematic alginate chain sequence (c).

(c) Chitosan

Chitosan is a linear polysaccharide with negative charge arising from its amine groups obtained by deacetylation of chitin. Chitosan can be isolated from crustacean shells, insect cuticles and the membranes of fungi. The properties of chitosan vary with its source. In order to achieve sufficient stability, chitosan gel beads and microspheres can be ionically cross-linked with polyphosphates and sodium alginate.^[64]

Advantages

- Show excellent biological properties such as biocompatibility, biodegradability, lack of toxicity, and adsorption, as well as relatively high percentage of nitrogen.^[65, 66]

Disadvantage

- It is water insoluble at a pH higher than 5.4. This insolubility presents the drawback of preventing the complete release of this biomaterial into the gut which pH is greater than 5.4.^[67]
- Antibacterial property of chitosan limits its use as coating material in encapsulation.^[68]




Fig 7: Chemical structure of Chitosan

(d) κ Carageenan

Carageenans are gel-forming and viscosifying polysaccharides, which are obtained by extraction from certain species of red seaweeds. All carrageenans are high-molecular-weight polysaccharides made up of repeating galactose units and 3,6 anhydrogalactose (3,6-AG), both sulfated and nonsulfated. The units are joined by alternating α -1, 3 and β -1,4 glycosidic linkages. κ -carrageenan requires high temperatures (60-90 °C) for dissolution, especially when applied at high concentrations such as 2-5%. However, this material used for encapsulating probiotics requires a temperature comprised between 40 and 50 °C at which the cells are added to the polymer solution. Beads by this polymer can be prepared by extrusion as well as emulsion technique.^[69, 70] Gelation of κ -carrageenan can also be performed using chemical method by reacting with monovalent ions such as potassium (KCl), providing brittle gel, with low ability to withstand stresses. Addition of KCl inhibits the growth of some lactic acid bacteria such as *Streptococcus thermophilus* and *L. delbrueckii* ssp. *Bulgaricus*^[71], which can be eliminated by the combination with locust bean gum with the ratio of κ -carrageenan to locust bean gum as 1:2.^[72]

Advantages: The encapsulation of probiotic cells in κ -carrageenan beads keeps the bacteria in a viable state.^[73]




Fig 8: Chemical structure of κ Carageenan

Dis Advantages

- Scale up difficulty
- Susceptibility to environment factors
- Lack of mechanical strength

(e) Xanthan gum

Xanthan gum is a microbial exopolysaccharide consisting of a cellulosic backbone with side chains of two mannose and one glucuronic acid on every second glucose residue.^[74,75] Xanthan gum is stable over a wide range of temperatures and pH, which finds many applications in food, pharmaceutical, cosmetic, and oil-drilling industries.^[76] Side chains of xanthan gum represent a very high proportion of the molecule (60%). Due to the side chains, the polymer completely hydrates in water.




Fig 9: Chemical structure of Xanthum gum

(f) Cellulose acetate phthalate

Cellulose acetate phthalate is most widely used encapsulating material due to its acid resistance. Its structure composes of cellulose polymer that 50% of hydroxyl groups esterified with acetyls and 25% is esterified with one or two carboxyls of a phthalic acid. It is soluble at $\text{pH} \geq 6$, but insoluble at $\text{pH} \leq 5$.^[77] Because of having a safe nature for purpose human ingestions, it is being widely used for drug capsulation in pharmacy.^[78, 41]

There are several studies which shows successful microencapsulation of probiotics using CAP can be achieved by both chemical and physical methods. For example, Rao et al. reported high survivability as high as 10^9 cfu mL^{-1} after incubation in simulated gastric juice of *B. pseudolongum* encapsulated in CAP using emulsion technique. The similar result was obtained from the studies of Favaro-Trindale and Grosso when *B. lactis* (Bb-12) and *L. acidophilus* (La-05) were encapsulated in CAP using spray drying method.

Advantage

- Insoluble at pH below 5 & soluble at pH above 6, thus suitable for microencapsulation of probiotic.^[79]

Disadvantage

- The disadvantage of CAP is that it cannot form gel beads by ionotropic gelation; only capsules have been developed by emulsification using this biomaterial.




Fig 10: Chemical structure of Cellulose acetate phthalate

(g) Gelatin

Gelatin is a mixture of peptides and proteins produced by partial hydrolysis of collagen extracted from the skin, bones, and connective tissues of animals such as domesticated cattle, chicken, pigs, and fish. Its chemical composition is, in many respects, closely similar to that of its parent collagen. Commercial gelatins can be divided into two groups depending on the treatment to obtain as type A (acid pre-treatment) and type B (basic pre-treatment).^[80] Gelatin is water-soluble, providing high viscosity. Gelation of gelatin is caused by conversion of random coil-helix when it is cooled.

Gelatin gum has been used for the microencapsulation of probiotics, alone or in mixture with other gums.^[81]

Advantages

- Gelatin has a very special structure and versatile functional properties, and forms a solution of high viscosity in water, which sets to a gel during cooling.^[82]
- Its amphoteric nature gives the ability of having synergistic effects with anionic polysaccharides such as gelatin gum.




Fig 11: Chemical structure of Gelatin

(h) Whey protein

Whey protein is the collection of globular proteins isolated from whey, a by-product of cheese manufactured from cow's milk. There are four main classes of proteins in whey: β -lactoglobulin, α -lactalbumin, serum albumin and several immunoglobulins. Most of these proteins have a globular conformation and are susceptible to denaturation and aggregation induced by heat and high pressure.^[83] Whey protein are obtain by ultrafiltration ,during which the low molecular weight compounds such as lactose, minerals, vitamins & non protein nitrogen are removed in the permeate while the proteins become concentrated in the retentate.Whey protein is very popular for film forming characteristics & is used as a protective material in spray drying, resulting in water soluble microcapsule system.^[84] They can be easily mixed with negatively charged polysaccharides such as alginate, carrageenan or pectin.^[85] Whey protein appears as a potential candidate as coating agent as it is entirely biodegradable and frequently used in many types of food products.

(i) Starch

Starch consists of D-glucose unit joint together with glycosidic bonds. It has been used as a material for coating of alginate capsules. High-amylose corn starch (HACS) can be applied for enhancing functions of capsule or shell/coat formation.^[86] Blending alginate with starch is a common practice and it has been shown that encapsulation effectiveness of different bacterial cells especially lactic acid bacteria were improved by applying this method.^[87] Lyophilized corn starch (LCS) has been reported to be used as capsule-forming material; however, it decomposes by pancreatic enzymes.^[88] Resistant starch (RS) is not degraded by the pancreatic amylase enters the intestine in the indigestible form. This specification apart from giving the microbeads good enteric delivery characteristic (good release of bacterial cells in the large intestine), also gives them prebiotic functionality as they can be used by the probiotic bacteria in the intestine.^[89] Consumption of resistant starch reduces the risk of intestinal cancer because of having dietary fiber functionality.^[90]




Fig 12: Chemical structure of Starch

Table 2: Different probiotic strain, biomaterial, and microencapsulation techniques

S.No	Probiotic	Encapsulation method	Encapsulating Material	Reference
1	<i>Lactobacillus acidophilus</i>	Spray drying	Chitosan	[91]
2	<i>Lactobacillus Plantrum</i>	Spray freeze drying	Whey Protein	[92]
3	<i>Lactobacillus casei</i>	Spray drying	Chitosan Calcium alginate	[93]
4	<i>L. rhamnosus</i>	Gel beads	Alginate	[61]
5	<i>L. casei</i>	Emulsification	Carrageenan/locust bean gum	[94]
6	Saccharomyces Boulardii	Emulsification	Alginate was blended with mucilage and inulin	[95]
7	<i>Bifidobacterium</i>	Gel beads	Alginate/chitosan	[64]
8	<i>Bifidobacterium</i>	Gel beads	Carrageenan/locust bean gum	[85,96]
9	<i>Bifidobacterium longum</i>	Extrusion	Alginate	[59]
10	<i>L. acidophilus</i> (La-05)	Gel beads	Cellulose acetate phthalate	[97]

CONCLUSION

Probiotics, live cells with different beneficiary characteristics, have been extensively studied and explored commercially in many different products in the world. Their benefits to human and animal health have been proven in hundreds of scientific research. Viability of probiotic bacteria in a product at the point of consumption is an important consideration for their efficacy, as they have to survive during the processing and Shelf life of food and supplements, transit through high acidic conditions of the stomach and enzymes and bile salts in the small intestine. Microencapsulation is most widely used technology to retain the potency of probiotic to be delivered orally into the GI system to maintain their potency. The viability of probiotics is a key parameter for developing probiotic food products. New technologies have been developed to enable high cell yield at large scale and ensure probiotic stability for a long period in food. In the food processing industry, preservation and storage, and micro-encapsulation will increasingly play a role to protect the viability and enhance the survival of bacteria against adverse environmental conditions.

Future research could be concentrated on the aspects such as applying more efficient encapsulation materials or improving the common used ones, The technology of micro-encapsulation, needs to be developed with more precise machinery, capsule and better delivery systems, *in vitro* and *in vivo* studies using human being should be carried out to confirm the efficacy of microencapsulated probiotics, We should also look forward to curtail cost and provide more cost effective techniques for Probiotic encapsulation .

Emerging and promising research work serving mankind for a better health is visualized for the microencapsulation of probiotics in the future.

REFERENCES

1. Hood SK. and Zottola EA. Effect of low pH on the ability of *Lactobacillus acidophilus* to survive and adhere to human intestinal-cells. *J Food Sci* 1988; 53:1514-1516.
2. Klaver FAM. et al., Growth and survival of bifidobacteria in milk. *Neth Milk Dairy J* 1993; 47:151-164.
3. Shah NP. and Lankaputhra WEV. Improving viability of *Lactobacillus acidophilus* and *Bifidobacterium* spp. in yogurt. *Int Dairy J* 1997; 7: 349-356.
4. Hughes DB, Hoover DG. Bifidobacteria: Their potential for use in american dairy products. *Food Technol* 1991; 45: 74-83.
5. Ahmed B. Mital BK. Effect of magnesium and manganese ions on the growth of *Lactobacillus acidophilus*. *J Food Technol* 1990; 27:228-229.
6. Babu V. et al. Effect of tomato juice addition on the growth and activity of *Lactobacillus acidophilus*. *Int J Food Microbiol* 1992; 17: 67-70.
7. Marshall VM. Inoculated ecosystems in a milk environment. *J Appl Bacteriol* 1992; 73:127-135.
8. Shah NP. Probiotic bacteria: Selective enumeration and survival in dairy foods. *J Dairy Sci* 2000; 83: 894-907.
9. Vidhyalakshmi R., et al., R.S. Encapsulation “The future of probiotics”: A review. *Advanced Laboratory Research In Biology* 2009; 39: 96-103.
10. Jankovic et al., Application of Probiotics in Food Products Challenges and New Approaches. *Curr Opin Biotechnol* 2010; 21: 175-181.
11. Vinderola, C.G., et al., 2000. Survival of probiotic microflora in Argentinian yoghurts during refrigerated storage. *Food Research International*. 33, 97-102.
12. Gismondo MR. et al. Review of probiotics available to modify gastrointestinal flora. *Int J Antimicrobial Agents* 1999; 12: 287-292.

13. Parker RB. Probiotics, the other half of the antibiotic story. *Anim nutr health* 1974; 29: 4-8.
14. Salminen S. et al. Demonstration of safety of probiotics – A review. *Int J Food Microbiol* 1998; 44: 93-106.
15. Marteau PR. et al. Protection from gastrointestinal diseases with the use of probiotics. *Am J Clin Nutr* 2001; 73: 430-436.
16. Reid G. et al. New scientific paradigms for probiotics and probiotics. *J Clin Gastroenterol* 2003; 37: 105-118.
17. McFarland LV. Meta-analysis of probiotics for the prevention of antibiotic associated diarrhea and the treatment of *Clostridium difficile* disease. *Am J Gastroenterol* 2006; 101:812- 822.
18. McFarland LV. Systematic review and meta-analysis of *Saccharomyces boulardii* in adult patients. *World J Gastroentero* 2010; 16: 2202-2222.
19. Whorwell, P.J., et al., Efficacy of an encapsulated probiotic *Bifidobacterium infantis* 35624 in women with irritable bowel syndrome. *Am J Gastroenterol* 2006; 101: 1581-1590.
20. Bausserman M. and Michail S. The use of *Lactobacillus GG* in irritable bowel syndrome in children: a double-blind randomized control trial *J Pediatr* 2005; 147:197-201.
21. Welters, C.F., et al., Effect of dietary inulin supplementation on inflammation of pouch mucosa in patients with an ileal pouch-anal anastomosis. *Dis Colon Rectum* 2002; 45: 621-627.
22. Lindsay JO. et al. Clinical, microbiological, and immunological effects of fructo-oligosaccharide in patients with Crohn's disease. *Gut* 2006; 55: 348-355.
23. Kalliomäki M. et al. Probiotics in primary prevention of atopic disease: a randomised placebo-controlled trial. *Lancet* 2001; 357: 1076–1079.
24. Reid G. et al. Oral probiotics can resolve urogenital infections. *FEMS Immunol Med Microbiol* 2001; 30: 49-52.
25. Falagas ME. et al. Probiotics for prevention of recurrent urinary tract infections in women. *Drugs* 2006; 66: 1253–1261.
26. Gotteland M. et al. Effect of *Lactobacillus* ingestion on the gastrointestinal mucosal barrier alterations induced by Indometacin in humans. *Aliment Pharmacol Ther* 2001; 15: 11-17.
27. Reid G. and Bruce AW. Selection of *Lactobacillus* strains for urogenital probiotic applications. *J Infect Dis* 2001; 183: 77-80.

28. Adlerberth I. A mannose-specific adherence mechanism in *Lactobacillus plantarum* conferring binding to the human colonic cell line HT-29. *Appl Environ Microbiol* 1996; 62: 2244-2251.
29. Mandel DR. *Bacillus coagulans*: A viable adjunct therapy for relieving symptoms of rheumatoid arthritis according to a randomized, controlled trial. *BMC Complement Altern Med*, 2010; 10-1.
30. Gupta, P., et al., Is *Lactobacillus GG* helpful in children with Crohn's disease? Results of a preliminary, open-label study. *J Pediatr Gastroenterol Nutr* 2000; 31: 453-457.
31. Guslandi M. et al. *Saccharomyces boulardii* in maintenance treatment of Crohn's disease. *Dig Dis Sci*, 2000; 45: 1462– 1464.
32. Ling WHL. et al. *Lactobacillus* strain GG supplementation decreases colonic hydrolytic and reductive enzyme activities in healthy female adults. *J Nutr*, 1994; 124: 18–23.
33. Bailey P. and Shahani K. 1979. Inhibitory effect of acidophilus cultured colostrum and milk upon the proliferation of ascites tumor. In Proceedings of the 71st Annual Meeting of the American Dairy Sci Association.
34. McIntosh, GH. A probiotic strain of *L. Acidophilus* reduces DMH-induced large intestinal tumors in male sprague-dawley rats. *Nutr Cancer* 1999; 35: 153-159.
35. Goldin BR. Gorbach SL. The effect of milk and *Lactobacillus* feeding on human intestinal bacterial enzyme activity. *Am J Clin Nutr* 1984; 39: 756–761.
36. Bogdanov IG. et al. Antitumour glycopeptides from *Lactobacillus bulgaricus* cell wall. *FEBS Letters*. 1975; 57: 3–8.
37. Gibbs B. et al Encapsulation in the food industry: a review. *Int J Food Sci Nutr* 1999; 50: 213-24.
38. Champagne CP. Fustier P. Microencapsulation for delivery of Probiotics and other ingredients in functional dairy products. *Func Dairy Prod* 2007; 2: 404-426.
39. Shah NP. Functional cultures and health benefits. *Int Dairy J* 2007; 17: 1262-1277.
40. Kailasapathy K. Microencapsulation of Probiotic Bacteria: Technology and Potential Applications 2002; 3: 39-48.
41. Krasaekoopt W. et al. Evaluation of encapsulation techniques of probiotics for yoghurt. *Int Dairy J* 2003; 13: 3-13.
42. Jackson, L.S., and Lee, K., Microencapsulation and the food industry. *Food sci. Technol* 1991; 24: 289-297.
43. Pikal MJ. Freeze-drying of protein, part-I: process design. *PharmTech Int* 1991; 1: 37-43.

44. Lankaputhra WEV. and Shah NP. Survival of *Lactobacillus acidophilus* and *Bifidobacterium* spp. in the presence of acid and bile salts. *J Cult Dairy prod* 1995; 30: 2-7.
45. Heidebach T. et al. Influence of casein based microencapsulation on freeze-drying and storage of probiotic cells. *J Food Eng* 2010; 98:309-316.
46. Chávez BE. Ledebor AM. Drying of Probiotics: Optimization of Formulation and Process to Enhance Storage Survival. *Drying Technology* 2007; 25: 1193-1201.
47. Sahasathian T. et al. Sustain release of amoxicillin from chitosan tablet. *Arch Pharmacol Res* 2007; 40: 526-531.
48. Wher, H.M., and Frank, J.F., 2004. Standard methods for the examination of dairy products. 17th ed. American Public Health Association, Washington.
49. Raymond C. Rowe et al. Acidic Acid, Handbook of Pharmaceutical Excipients (Rowe, Handbook of Pharmaceutical Excipients) (Sixth ed.), Pharmaceutical Pr, 2009; 11–12, ISBN 0-85369-792-2.
50. Dong Z. et al. Alginate/gelatin blend films and their properties for drug controlled release. *J Membr Sci* 2006; 280: 37-44.
51. Draget KI. et al. Na⁺ and K⁺-alginate effect on Ca²⁺ gelation. *Carbohydr Polym* 1998; 35: 1-6.
52. Chandramouli V. et al. An improved method of microencapsulation and its evaluation to protect *Lactobacillus* spp. in simulated gastric conditions. *J Microbiol Methods* 2004; 56: 27-35.
53. Dimantov A. et al. Study of high amylose corn starch as food grade enteric coating in a microcapsule model system. *Innov food sci & emerg Technol* 2003; 5: 93-100.
54. Gouin S. Microencapsulation: industrial appraisal of existing technologies and trends. *Trends Food Sci Technol* 2004; 15: 330-347.
55. Sheu TY. and Marshall RT. Improving culture viability in frozen dairy desserts by microencapsulation. *J Dairy Sci* 1991; 74: 107-111.
56. Sheu TY and Marshall RT. Micro entrapment of lactobacilli in calcium alginate gel. *J Food Sci* 1993; 54: 557-561.
57. Kim IK. et al. Effects of dehydration media and immobilization in calcium-alginate on the survival of *Lactobacillus casei* and *Bifidobacterium bifidum*. *Korean J Food Sci Technol* 1996; 18: 193-198.
58. Khalil AH. and Mansour EH. Alginate encapsulated bifidobacteria survival in mayonnaise. *J Food Sci* 1998; 63: 702-705.

59. Lee KY, Heo TR. Survival of *Bifidobacterium longum* Immobilized in Calcium Alginate Beads in Simulated Gastric Juices and Bile Salt Solution. *Appl Environ Microbiol* 2000; 66: 869-873.
60. Eikmeier H, Rehm HJ. Stability of calcium-alginate during citric acid production of immobilized *Aspergillus niger*. *Appl Microbiol Biotechnol* 1987; 26:105-111.
61. Krasaekoopt W. et al. Survival of probiotics encapsulated in chitosan-coated alginate beads in yoghurt from UHT- and conventionally treated milk during storage. *Lwt-Food Sci Technol* 2006; 39: 177-183.
62. Truelstrup, HL. et al., Survival of Ca-alginate microencapsulated *Bifidobacterium* spp. in milk and simulated gastrointestinal conditions. *Food Microbiol* 2002; 19: 35–45.
63. Sun W, Griffiths MW. Survival of bifidobacteria in yogurt and simulated gastric juice following immobilization in gellan-xanthan beads. *International J Food Microbiol* 2000; 61: 17-25.
64. Lee JS. et al. Survival of freeze-dried *Lactobacillus bulgaricus* KFRI 673 in chitosan-coated calcium alginate micro particles, *J Agric Food Chem* 2004; 52: 7300-7305.
65. Dutta PK. et al. Chitin and chitosan: Chemistry, properties and applications. *J Sci Ind Res* 2004; 63: 20-31.
66. Sashiwa H. and Aiba SI. Chemically modified chitin and chitosan as bio-materials. *Prog Polym Sci* 2004; 29:887-908.
67. Hugué ML. et al. Calcium-alginate beads coated with polycationic polymers: Comparison of chitosan and DEAE-Dextran. *Process Biochem* 1996; 31: 347-353.
68. Sudarshan NR et al. Antibacterial action of chitosan. *Food Biotechnol* 1992; 6: 257-272.
69. Mangione MR. et al. Thermoreversible gelation of κ -Carrageenan: relation between conformational transition and aggregation. *Biophys Chem* 2003; 104: 95-105.
70. Mangione MR. et al. K^+ and Na^+ effects on the gelation properties of κ -Carrageenan. *Biophys Chem* 2005; 113:129-135.
71. Audet P. et al. Immobilized growing lactic acid bacteria with κ -carrageenan-locust bean gum gel. *Appl Microbiol Biotechnol* 1988; 29: 11-18.
72. Audet P. et al. Batch fermentations with a mixed culture of lactic acid bacteria immobilized separately in κ -carrageenan locust bean gum gel beads. *Appl Microbiol Biotechnol* 1990; 32: 662-668.
73. Dinakar P, Mistry VV. Growth and viability of *Bifidobacterium bifidum* in cheddar cheese. *J Dairy Sci* 1994; 77: 2854-2864.

74. Jansson P. et al. Structure of extracellular polysaccharide from *Xanthomonas campestris*. *Carbohydr Res* 1975; 45:275-282.
75. Melton LD. et al. Covalent structure of the polysaccharide from *Xanthomonas campestris*: evidence from partial hydrolysis. *Carbohydr Res* 1976; 46: 245-257.
76. Meyer EL. et al., Investigation of xanthan gum solution behavior under shear flow using rheo optical techniques. *Macromol* 1993; 26:504-511.
77. Malm CJ. et al. Cellulose acetate phthalate as enteric coating material. *AAPS* 1951; 10: 520-522.
78. Rao AV. et al. Survival of microencapsulated *Bifidobacterium pseudolongum* in simulated gastric and intestinal juices. *Can Inst Food Sci Technol* 1989; 22: 345-349.
79. Anal AK. Singh H. Recent advances in microencapsulation of probiotics for industrial applications and targeted delivery. *Trends Food Sci Technol*, 2007; 18: 240-251.
80. Poppe J. *Gelatin, Thickening and Gelling Agents for Food*, Blackie Academic and Professional, 2nd edition, 1997; 144–168.
81. Hyndman, C.L., et al., Microencapsulation of *Lactococcus lactis* with cross-link gelatin membranes. *J Chem Technol Biotechnol* 1993; 56: 259-263.
82. Rokka S. and Rantamaki P. Protecting probiotic bacteria by microencapsulation: Challenges for industrial applications. *Eur Food Res Technol* 2010; 231: 1-12.
83. Hambling SG. et al. *Beta-Lactoglobulin in Advanced Dairy Chemistry: Proteins*. P.F.E. Fox, Editor. Elsevier Applied Science Publishers: London 1992; 141-190.
84. Picot A. and Lacroix C. Encapsulation of *Bifidobacteria* in whey protein based microcapsules and survival in simulated gastrointestinal conditions and in yoghurt. *Int dairy J* 2004; 14: 505-515.
85. Doleyres Y. et al. *Bifidobacterium longum* ATCC 15707 cell production during free- and immobilized-cell cultures in MRS-whey permeate medium. *Appl Microbiol Biotechnol* 2002; 60: 168-173.
86. Lian W. et al. Survival of *bifidobacteria* after spray-drying. *Int J Food Microbiol* 2002; 74: 79-86.
87. Sultana K et al. Encapsulation of probiotic bacteria with alginate-starch and evaluation of survival in simulated gastrointestinal conditions and in yoghurt. *Int J Food Microbiol* 2000; 62: 47-55.
88. Fanta GF. et al. Starch microcapsules for delivery of active agents. US patent 2001; 6: 238-677.

89. Haralampu SG. Resistant starch-a review of the physical properties and biological impact of RS3. *Carbohydr Polym* 2000; 41: 285-292.
90. Dimantov A. et al. Surface characterization and dissolution properties of high amylase core starch pectin coatings. *Food Hydrocol* 2004; 18: 29-37.
91. Yonekura L. Microencapsulation of *Lactobacillus acidophilus* NCIMB 701748 in matrices containing soluble fibre by spray drying: Technological characterization, storage stability and survival after in vitro digestion. *J Func Foods* 2014; 6: 205-214.
92. Dolly P. et al. Microencapsulation of *Lactobacillus plantrum* by spray-freeze-drying method and evaluation of survival in simulated gastrointestinal conditions. *J Microencapsulation* 2011; 28:568-74.
93. Ivanovska TP. Microencapsulation of *Lactobacillus casei* in chitosan alginate microparticles using spray drying method *Vol* 2012; 31, No 1.
94. Adhikari K. Mustapha A. Grun IU. Survival and metabolic activity of microencapsulated *Bifidobacterium longum* in stirred yogurt. *J Food Sci* 2003; 68: 275-280.
95. Zamora-Vega, R., et al., Effect of incorporating prebiotic in coating material for the microencapsulation of *Saccharomyces boulardii*, *Int J Food Sci Nutr* 2012; 63: 930-5.
96. Doleyres Y. et al. Continuous production of mixed lactic starters containing probiotics using immobilized cell technology. *Biotechnol Progr* 2004; 20: 145–150.
97. Trindade F and Grosso CRF. Microencapsulation of *L. acidophilus* (La- 05) and *B.Lactis* (Bb-12) and evaluation of their survival at the pH values of the stomach and in bile. *J of Microencapsulation* 2002; 19: 485-494.