




airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

S1 1401 EN


Technical Data Sheet - Product Information

Product: TOP SPRAY SCHWARZ



Characteristics:

Black under seal coating based on rubber and synthetic resin.
Fast drying and overcoatable.
Free of asbestos and chlorinated hydrocarbons.



Range of application:

Car and industrial lacquering

Instructions for use:

Clean surface thoroughly from grease and dust.
Remove rust and loose paint layers with a wire brush and/or sandblast.

Prior to application shake the can thoroughly.

Apply airo TOP SPRAY crosswise and keep a spraying distance of about 30 cm.
If several layers are needed allow for a flash off time of several minutes between each layer.
After drying the coat can be varnished with all lacquers commonly used in car refinishing industry.

Drying time: 20 to 30 minutes depending on film thickness.

Note:

To avoid a decrease of the spray pressure shake the can between the application steps.

Chemical basis:

TOP SPRAY: Rubber, synthetic resin, filling material, thixotropic agents, solvents.
Propellant: propane, butane

Temperature conditions:

Material and surrounding temperatures should range between +18 °C and +25 °C.
Do not apply at temperatures below +15 °C

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Disposal consideration:

Disposal of according to local regulations.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.



airo-chemie
A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870

SA 1401 EN


Technical Data Sheet - Product Information

Product: **TOP SPRAY GRAU**



Characteristics:

Grey under seal coating based on rubber and synthetic resin.
Fast drying and overcoatable.
Free of asbestos and chlorinated hydrocarbons.



Range of application:

Car and industrial lacquering

Instructions for use:

Clean the surface thoroughly from grease or dust.
Remove rust and loose paint layers with a wire brush and / or sand blast.

Prior to application shake the can thoroughly.

Apply airo TOP SPRAY crosswise and keep a spraying distance of about 30 cm.
If several layers are needed allow for a flash off time of several minutes between each layer.
After drying the coat can be varnished with all lacquers commonly used in the car refinishing industry.

Drying time: 20 to 30 minutes depending on film thickness.

Note:

To avoid a decrease of the spray pressure shake the can between the application steps.

Chemical basis:

TOP SPRAY: Rubber, synthetic resin, filling material, thixotropic agents, solvents.
Propellant: propane, butane

Temperature conditions:

The material and surrounding temperature should range between +18 °C and +25 °C.
Do not apply at temperatures lower than +15 °C

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Disposal consideration:

Disposal according to local regulations.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.