



## 5600 Air-Dry Clear

**ACCELERO****North American Market Only**


### Description:

Accelero 5600 is a conventional scratch resistant Air-Dry Clearcoat with premium finishing properties. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. It can be simply flattened and polished after 1 hour at application temperature.

It uses the same GenMax hardener family (H1522, H2232, H3236) as other premium clearcoats in the GenMax range, providing a complete and compact offer.

### Suitable Substrates:


- “General” GenRock Basecoat.
- “General” Gen<sub>2</sub>O Basecoat.
- “General” GenVerde Basecoat.



Mix 2:1:10-15% with H1522, H2232, H3236 GenMax hardener and reducer

100%	50%	10-15%
5600	H1522 2K HARDENER FAST	S1522 REDUCER
<b>5600</b>	<b>H2232 2K HARDENER NORMAL</b>	<b>S2232 REDUCER*</b>
5600	H3236 2K HARDENER SLOW	S3236 REDUCER

*\*Recommended*



17-19 s / DIN 4 mm / 20°C (68°F)

Potlife: 60 minutes at 20°C (68°F)



HVLP 1.2 – 1.3 mm



1 medium + 1 full coat  
3-5 minutes between coats  
35 – 45 micron  
2.0 – 2.2 bar inlet pressure



Dust free after	15 minutes @ 25 °C (77°F) 25 minutes @ 20 °C (68°F)
-----------------	--

Touch free after	20 minutes @ 25 °C (77°F) 45 minutes @ 20 °C (68°F)
------------------	--

Sandable & Polishable after	60 minutes @ 25 °C (77°F) 90 minutes @ 20 °C (68°F)
-----------------------------	--

General Paint Co.

P.O.Box: 7623 Beirut - Lebanon - Tel: 09 925991/2 - Fax: 09 925993 - e-mail: [info@generalpaint.biz](mailto:info@generalpaint.biz)

Product Data Sheet



## 5600 Air-Dry Clear

**ACCELERO**

North American Market Only



5 Minutes at 60°C (140 °F) Panel Temperature.



5-7 minutes, depending on color.

Substrate temperature 80°C-100°C (176°F to 212°F)

*\*Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.*



Wear suitable protection

**Specific Gravity:** 0.994 kg/ cm<sup>3</sup> (8.29493 lbs/gal)

**Flash Point:** 25°C (77°F)

**Solids Content:** Approximately 48 % by weight RFU

**Coverage:** 7-8 m<sup>2</sup>/l at 35-45 micron film thickness (theoretical)

**SDS:** Refer to the safety data sheet

Product Data Sheet