



**The Performance Choice**



**THERM-X 30**

	Single Pane	Dual Pane
Visible Light Transmission (%)	30	27
Visible Light Reflectance (%)	47	47
Infrared Rejection (%)	93	94
UV Light Rejection (%)	99.9	99.9
Total Solar Energy Rejected (%)	72	65
Shading Coefficient	0.32	0.42
Solar Heat Gain Coefficient	0.28	0.35
Glare Reduction (%)	65	64
Winter Median U-Value	0.93	0.46

[www.huperoptikusa.com](http://www.huperoptikusa.com)



Performance data is based on this film being applied to the inside of 3mm clear glass. All data calculated using the definitions and equations in ISO9050 & ASHARE Handbook. The data is subject to variations within industry standards.  
Copyright © 2008 Hüper Optik® USA ([www.huperoptikusa.com](http://www.huperoptikusa.com)), 5821 West Sam Houston Parkway North Suite 400, Houston, TX 77041; phone: 888.296.3456; fax: 832.467.1190



Meister Keramische Technologie