


**HÜPER OPTIK®**  
Nano-Ceramic Window Films



**Energy Saving  
Performance 35**



**ENERGY SAVER CERAMIC 35**

Visible Light Transmission (%)	34
Visible Light Reflectance (%)	15
Infrared Rejection (%)	81
UV Light Rejection (%)	99.9
Total Solar Energy Rejected (%)	61
Shading Coefficient	.45
Solar Heat Gain Coefficient	.39
Glare Reduction	61

[www.huperoptikusa.com](http://www.huperoptikusa.com)



Performance data is based on this film being applied to the inside of 3mm clear glass. All data calculated using the definitions and equations in ISO9050 & ASHARE Handbook. The data is subject to variations within industry standards.  
Copyright © 2008 Hüper Optik® USA ([www.huperoptikusa.com](http://www.huperoptikusa.com)), 5821 West Sam Houston Parkway North Suite 400, Houston, TX 77041; phone: 888.296.3456; fax: 832.467.1190



Meister Keramische Technologie

HSPE-ESC35