

HÜPER OPTIK®



Physical Properties:

- 1 ply Safety/Security
- Film Thickness 4 mil.
- Film Structure 4 mil.
- Peel Strength: 5-7 lb/inch
- Adhesive Type: PS
- Tensile Strength: 28000 psi

CLEAR SHIELD 4

Visible Light Transmission (%)	88
Visible Light Reflectance (%)	9
Shading Coefficient	0.94
Total Solar Transmission (%)	77
UV Light Rejection (%)	99
Total Solar Energy Rejected (%)	18
Solar Heat Gain Coefficient	0.82

www.huperoptikusa.com



Performance data is based on this film being applied to the inside of 3mm clear glass. All data calculated using the definitions and equations in ISO9050 & ASHARE Handbook. The data is subject to variations within industry standards. Copyright © 2009 Hüper Optik® USA (www.huperoptikusa.com), 5821 West Sam Houston Parkway North Suite 400, Houston, TX 77041; phone: 888.296.3456; fax: 832.467.1190



Meister Keramische Technologie

HSPE-SC4