



SpECcell Polyethylene 40

CLOSED CELL POLYETHYLENE FOAM JOINT FILLER BOARD

DESCRIPTION

SpECcell Polyethylene 40 is a high performance closed cell polyethylene foam joint filler. It is suitable for use as an expansion joint filler in concrete, brickwork and blockwork, and in isolation joints where a readily compressible low load transfer joint filler is required.

TYPICAL USES

- Structural expansion joints in concrete, brick and blockwork
- Isolation joints to infill panels
- As a back-up support for sealants
- As a bond breaker for sealants over bituminous joint fillers
- Anti-vibration pads for machinery bases

ADVANTAGES

- Non-absorbent, closed cell
- Readily compressible
- Rot proof
- Deformable - accepts temperature cycle with minimal load transfer
- Non-tainting, suitable for potable water applications
- Excellent recovery after compression
- Resilient - will not distort under normal load from wet concrete
- Easily worked - can be cut with a knife
- Economical in use
- Bitumen free - suitable for use with elastomeric sealants
- Chemical resistant - inert to most dilute acids and alkalis; resistant to oil and hydrocarbons

RELEVANT STANDARDS

SpECcell Polyethylene 40 meets or exceeds the requirements of the following specifications:

- ASTM D1752 (extrusion and recovery at 50% compression)
- U.K. Department of Transport Specification for

Highway Works Part 3 - Clause 1015.1991

- U.K. DOE Specs for Road & Bridge Works - Clause 2630
- BS 5628 Part 3: 2001
- ASTM D 3575-08
- U.K. Department of the Environment General Specification 201, Clause 606

TECHNICAL DATA

Colour	White
Density	40 kg/m ³
Water absorption by volume	<0.55%
Compressive strength	>0.15 N/mm ²
Recovery at 50% comp.	>90%
Extrusion on 50% comp.	<6.6mm
Operating temperature	-40 °C to 70 °C
Fire effect	SpECcell Polyethylene 40 will melt in fire; the rate of spread of flame is minimized when confined in a joint
Compression loading	Meets the requirements of BS 5628 Part 3

APPLICATION

SpECcell Polyethylene 40 is a compressible joint filler in sheet form, used to form and fill expansion joints.

In Concrete:

SpECcell Polyethylene 40 can be placed against formwork on the concreting side prior to placing the first section of concrete and is left in place on removal of the formwork. The subsequent pour is then cast directly against the **SpECcell Polyethylene 40**. The board is then cut back later to form the sealing slot.

In Blockwork and Brickwork:

SpECcell Polyethylene 40 should be installed, whilst laying brick or blockwork, in such a way that a sealing slot, of the required dimensions is formed.

PACKAGING & YIELD

SpECcell Polyethylene 40 is available in a range of sizes to suit all site requirements (Board size 1m x 2m, Thickness 10, 15, 20, 25, 50, 100 mm...)

STORAGE & SHELF LIFE

Indefinite when stored in cool and dry conditions.

HEALTH & SAFETY

There are no health hazards associated with the normal use of **SpECcell Polyethylene 40**.

Issue 7B: 05/2021

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: info@spec.ae

www.spec.ae