

ALUMINIZED LACQUER
M 815091/S



Product Aluminized Lacquer For Treatment Of Printed Sheets

Code M 815091/S

SPECIFICATIONS

Viscosity 120-130 Sec .NO. Ford 4 At 25 °C.

Solids 35±2% (30min/200°)

SP. GR. 0.97 – 0.99 %

Flash Point Above 80 °C

INFORMATION

Type Epoxy Modified-Phenolic

Substrate Tinplate, Tin-Free Steel

Stoving 200 C For 10-15 Min. Peak Temperature

Dry – Film 7-8 GMS / Sq. METER

Wet – Film 8 -20 GMS / Sq. METER

Thinner AD 1408

Shelf Life 6 Months At 20°C

Remarks Stir Well Before Use
Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.



PACHIN :CAN COATINGS INK DATASHEET