

INTERNAL RED SPRAY LACQUER



Product	Modified Int. Red Lacquer Spray For Food Contacts
Code	M 6001

SPECIFICATIONS

Viscosity	90 -100 Sec .NO. Ford Cup 4 At 25°C.
Solids	35-38% (30min/200°)
SP. GR.	1.2 – 1.24 %
Flash Point	Above 80°C

INFORMATION

Uses	Interior Spray Lacquer For Drums
Substrate	Steel
Stoving	200 C For 15-20 Min. Peak Temperature
Dry – Film	11.5-16 GMS / Sq. METER
Wet – Film	25 –30 GMS / Sq. METER
Thinner	AD 1440
Shelf Life	6 Months At 20°C
Remarks	Stir Well Before Use Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.

