

INTERNAL BIEG LACQUER
M 6099



Product Internal Bieg Lacquer For Drums /Cans

Code M 6099

SPECIFICATIONS

Viscosity 140-160 Sec . Ford Cup NO. 4 At 25°C.

Solids 50±2 % (30min/200°)

SP. GR. 1.2 – 1.24 %

Flash Point Above 80°C

INFORMATION

Type Epoxy – Phenolic

Substrate Tinplate –Tin-Free Steel

Uses Internal Beige Enamel .
It Used As Double Coat.

Stoving 180-200 C For 15-20 Min

Dry – Film 10– 14 GMS / Sq. METER

Thinner AD 1408

Shelf Life 6 Months At 20°C

Remarks Stir Well Before Use
Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.



PACHIN :CAN COATINGS INK DATASHEET