

INTERNAL SPRAY GOLD LACQUER
MP 7080



Product Internal Spray Gold Lacquer For Collapsible Tubes

Code MP 7080

SPECIFICATIONS

Viscosity 70-80 Sec . Ford Cup NO. 4 At 25 °C.

Solids 40-45 % (30min/200)

SP. GR. Above 32 °C

Flash Point Above 80 °C

INFORMATION

Dry – Film 6– 10 GMS / Sq. METER

Thinner AD 1440

Type Epoxy – Phenolic

Substrate Aluminum

Uses Internal Gold For Al.Tubes
This Lacquer Combines High Characteristics Of Flexibility And Substrate Adhesion With A Good Resistance To The Most Critical Heat Treatments .

Shelf Life 6 Months At 25 °C

Remarks Stir Well Before Use
Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.



PACHIN :CAN COATINGS INK DATASHEET