

SIZE VARNISH M 815091



Product Transparent Under Lacquer For Deep Drawn Cans

Code M 815091

SPECIFICATIONS

Viscosity 100 -110 Sec .NO. Ford CUP 4 At 25°C.

Solids 30-35% (30min/200°)

INFORMATION

Stoving 170-200 C For 12-15 Min. Peak Temperature

Thinner AD 1408

Shelf Life 6 Months At 20°C

Remarks Stir Well Before Use
Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.



PACHIN :CAN COATINGS INK DATASHEET