TONED WHITE ENAMEL GL 70

Product	Toned White Enamel
Code	GL 70

SPECIFICATIONS

Viscosity	170-180 Sec . Ford Cup NO. 4 At 25°C.
Solids	55-58 % (30min/200°)
SP. GR.	1.25 – 1.29%
Flash Point	Above 90 °C

INFORMATION

Type	Acrylic White Enamel
Substrate	Tinplate And Tin-Free Steel
Uses	External White Enamel
Stoving	190-200 C For 12-15 Min. Peak Temperature
Dry – Film	12 – 14 GMS / Sq. METER
Wet – Film	18 –25 GMS / Sq. METER
Thinner	AD 1408 (Don’t Use Any Other Reducer)
Shelf Life	6 Months At 20°C
Remarks	Stir Well Before Use Do Not Expose To Direct Sun Light



Although The Fasts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.

PACHIN :CAN COATINGS INK DATASHEET