

WHITE INTERNAL ENAMEL

GL 40



Product White Internal Enamel

Code GL 40

SPECIFICATIONS

Viscosity 150-170 Sec .NO. Ford 4 At 25°C.

Solids 47+50 % (30min/200°)

SP. GR. 1.2 – 1.24 %

Flash Point Above 90 °C

INFORMATION

Type Epoxy

Substrate Tinplate, Tin-Free Steel

Uses Internal White Lacquer For Wide Range Of Food And Tomato Canning Industry It Has An Excellent Product And Scratch Resistance. Also It Can Be Used For Can Bodies And Can Ends.

Stoving 200 C For 10-15 Min. Peak Temperature

Dry – Film 14-16 GMS / Sq. METER

Wet – Film 25 –30 GMS / Sq. METER

Thinner AD 1408

Shelf Life 6 Months At 20°C

Remarks Stir Well Before Use
Do Not Expose To Direct Sun Light

Although The Facts And Suggestions In This Publication Are Based On Our Own Research And Are Believed Reliable. We Cannot Assume Any Responsibility For Performance Or Results Obtained Through The Use Of Our Products Herein Described . Nor Do We Accept Any Liability For Loss Or Damages Directly Or Indirectly Caused By Our Products . The User Is Held To Check The Quality , Safety , And All Other Properties Of Our Product Prior To Use. Nothing Herein Is To Be Taken As Permission , Inducement Or Recommendation To Practice Any Patented Invention Without A License.



PACHIN :CAN COATINGS INK DATASHEET