

باكشيلد - أنتي كاربونيشن ٨٩٥

الوصف

أنتي كاربونيشن ٨٩٥ من باكين ١٠٠٪ أكريليك مما يوفر حماية خارجية فائقة ومقاومة المياه ومقاومة الإتساع والتشقق. تكنولوجيا باكشيلد ٨٩٥ المتقدمة تتواءم مع خواص الميكانيكية المميزة التي مكنته ان يجتاز العديد من الإختبارات مثل الإستطالة، النزغ، التشقق، نفاذية ثاني أكسيد الكربون وبخار الماء تلك الخواص المطلوبة لهذا النوع من الدهان.

المميزات

تجعله مقاوم للتشقق

مقاوم للإتساع

مقاوم للكيمويات وخاصة ثاني أكسيد الكربون في الظروف القاسية

طريقة التنفيذ

يجب أن يكون السطح سليماً، نظيفاً خالياً من الأتربة والزيوت والشحوم إلخ. كل الأجزاء الغير متماسكة يجب أن تزال، في حالة الأسطح المجيرة والتربة يجب أن تزال بفرشاة ذات شعر خشن قوي. باكشيلد ٨٩٥ يخفف بنسبة ٢٠٪ - ٢٥٪ بالماء ويستخدم كبرايمر لسد المسام للأسطح الجديدة..

PachiShield - Anti Carbonation 895

Description:

Anti-Carbonation 895 is made entirely of acrylic and offers the best external protection against water, filth, and fracture resistance.

The unique mechanics of PACHI Shield 895 combined with the state-of-the-art technology allow it to pass several tests, including elongation, stripping, cracking, and permeability to carbon dioxide and water vapor, which are essential qualities for this type of paint.

Features :

Make it crack resistant

anti-fouling

Resistant to chemicals, especially carbon dioxide, in hard conditions

Recommended Use :

The surface must be intact, clean and free from dust, oil and grease etc.

All loose parts must be removed, in the case of silty surfaces and soils with a strong bristle brush.

Pachi shield 895 Dilute 20% - 25% with water

It is used as a primer to close pores for new surfaces.

أدوات الاستخدام

الفرشاة / الرولة / مسدس الرش



Application Tools

Brush / Roller / Spray gun

زمن الجفاف



جفاف سطحي ٤-٥ ساعة

جفاف كامل ٢٤ ساعة

الصلاحية



٢٤ شهر

شروط التخزين



بعيداً عن أشعة الشمس

التخفيف



يخفف بنسبة ٢٠٪ - ٢٥٪ بالماء

معدل الفرد



٢-٣ م / لتر عند 100 ميكرون

سمك فيلم جاف.

Drying Time

Surface dry 4 - 5 hr Through dry

24 hrs

Expiry

24 Months

Storage

Away from sunlight

Dilution

Tap water up to 20% to 25%

Coverage

from 2-3 m2 / Ltr at film

thickness 100 micron

Technical Data :

الخواص الفنية:

المظهر	مط Matt	Finish
اللون	أبيض وألوان حسب كارتة ألوان باكين	Colors
نسبة المواد الصلبة بالحجم	43 % ± 2	Solids by volume
نسبة المواد الصلبة بالوزن	1.32 ± 0.05	Solids by weight

أنتج طبقاً للمواصفات القياسية المصرية رقم ١٥٣٩ / ٢٠٢

Conforms to Egyptian standard 1539/2021

