


# Metallgießtemperatur metal casting temperature



°C	400	500	600	700	800	900	1.000	1.100	1.200	1.300	1.400	1.500
°F	750	930	1.110	1.290	1.470	1.650	1.830	2.010	2.190	2.370	2.550	2.730

Zink zinc	Zinklegierungen zinc alloys	Aluminiumlegierungen aluminium alloys	Gold gold Silber silver	Bronze bronze Messing brass	Kupfer copper Nickelbronze cupro-nickel	Gusseisen cast iron
--------------	--------------------------------	--	----------------------------------	--------------------------------------	--	------------------------