

WhiteCap Resources, LLC

Chemical Analysis

St. Peters Sandstone

| | |
|--|--------|
| Na₂O (%) | 0.0013 |
| MgO (%) | 0.0131 |
| Al₂O₃ (%) | 0.0263 |
| SiO₂ (%) <small>Calculated</small> | 99.92 |
| K₂O (%) | 0.0153 |
| CaO (%) | 0.0064 |
| TiO₂ (%) | 0.0059 |
| Fe₂O₃ (%) | 0.0166 |

