elastron®

COLUMBIA HYDRO

UPHOLSTERY

Natural Leather

TECHNICAL DATASHEET	TEST METHOD PRÜFVERFAHREN METHOD TEST MÉTODO DE PRUEBA	MEASUREMENT UNIT MAßEINHEIT UNIT OF MEASUREMENT UNIDAD DE MEDIDA	GUARANTEED GARANTIERT INSURED GARANTIZADA
BURNING BEHAVIOUR TO CIGARETTE AND MATCH FLAME **BRANDVERHALTEN GGÜ. ZIGARETTENGLUT UND STREICHHOLZFLAMME** **COMPORTEMENT DE COMBUSTION DES CIGARETTES ET ALLUMETTES** **COMPORTAMIENTO FRENTE AL FUEGO Y LLAMA**	BS 5852:1979 BS EN 1021-1-2:2006	FIRE RETARDANT	PASS
COLOUR FASTNESS TO RUBBING | DRY 50 CYCLES **ABRIEBFESTIGKEIT** | TROCKEN 50 ZYKLEN **RÉSISTANCE AUX FROTTEMENTS** | A SEC 50 CYCLES **SOLIDEZ DEL COLOR AL FROTE** | A SECO 50 CICLOS	UNI EN ISO 11640:1998	GREY SCALE	≥ 3
COLOUR FASTNESS TO RUBBING | WET 10 CYCLES **ABRIEBFESTIGKEIT** | NASS 10 ZYKLEN **RÉSISTANCE AUX FROTTEMENTS** | HUMIDE 10 CYCLES **SOLIDEZ DEL COLOR AL FROTE** | MOJADO 10 CICLOS	UNI EN ISO 11640:1998	GREY SCALE	≥ 3
TEAR STRENGTH | SINGLE EDGE TEAR **REIßFESTIGKEIT HOSE** | EINKANTENRISS **RÉSISTANCE AU DÉCHIREMENT** | BORD UNIQUE **RESISTENCIA AL DESGARRO** | DESGARRO SIMPLE	UNI EN ISO 3377-1	N	≥ 20
HYDRO REPELLENT **WASSERABWEISEND** **HYDRO RÉPULSIF** **HIDRO REPELENTE**			
COLOUR FASTNESS TO ARTIFICIAL LIGHT | EXPOSITION ENERGY 16.000 kj/sqm **UV-BESTÄNDIGKEIT** | EXPOSITIONS ENERGIE 16.000 kj/qm **RÉSISTANCE À LA LUMIÈRE ARTIFICIELLE** | ÉNERGIE D'EXPOSITION 16.000 kj/m² **SOLIDEZ DEL COLOR A LA LUZ ARTIFICIAL** | EXPOSICIÓN A ENERGÍA 16.000 kj/m²	UNI EN ISO 105 B02 (MET.5)	GREY SCALE	≥ 2

ORIGIN RAW MATERIAL

EUROPEAN BOVINE ORIGIN, NATURAL GRAIN - NABUK FINISHING
ANILINE DYED - SUEDE LOOK, SOFT AND VELVET TOUCH

1.2 - 1.4 mm THICKNESS | 5.0 sqm AVERAGE

REACH COMPLIANT - RESPECTS THE ENVIRONMENT USING APPLICATION OF NEW TECHNOLOGIES IN THE PRODUCTION PROCESS

CLEAN AND CARE RECOMMENDATIONS

TO REMOVE DUST USE A VACUUM CLEANER.

AVOID EXPOSING DIRECTLY TO SUNLIGHT AND HEAT SOURCES.

ANY STAIN, SPILLS OR SOILING SHOULD BE CLEANED UP PROMPTLY WITH A NEUTRAL SOAP SOLUTION USING A CLOTH IN SMOOTH CIRCULAR MOVEMENTS.

WE DO NOT ACCEPT RESPONSIBILITY FOR ANY DAMAGE RESULTING FROM INAPPROPRIATE USE, CHEMICAL CLEANING OR ADDITIONAL IMPREGNATION.

DELIVERY AND SHIPPING

4/5 DAYS DELIVERY TIME

EXPRESS SERVICE - READY TO SHIP IN 48h

WORLDWIDE SHIPPING AVAILABLE