APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A467	**WHITE URETHANE** **BARE 7000 SERIES AND 2219 ALUMINUM ALLOYS** A SULFURIC ACID ANODIZE ALL SURFACES PER 112. B PRIME ONE COAT ALL SURFACES PER 201. C PAINT WITH WHITE URETHANE COATING ALL SURFACES PER 223 (OR 274). D TOUCH UP AS REQUIRED PER 237. E (SEE A466 FOR PREFERRED CODE). NOTE: DO NOT USE WITHOUT MATERIALS & PROCESSES ENGINEERING APPROVAL.
A468	**WHITE URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS (FOR ASSEMBLIES REQUIRING PRESS FITS)** A ANODIZE ALL SURFACES PER 111. B PRIME ONE COAT ON SPECIFIED SURFACES PER 202. C PAINT WITH WHITE URETHANE COATING ON THE PRIMED SURFACES PER 222 (OR 274). D TOUCH UP AS REQUIRED PER 237.
A469	**WHITE URETHANE** **BARE 7000 SERIES AND 2219 ALUMINUM ALLOYS (FOR ASSEMBLIES REQUIRING PRESS FITS)** A SULFURIC ACID ANODIZE ALL SURFACES PER 112. B PRIME ONE COAT SPECIFIED SURFACES PER 202. C PAINT WITH WHITE URETHANE COATING ON THE PRIMED SURFACES PER 222 (OR 274). D TOUCH UP AS REQUIRED PER 237. E (SEE A468 FOR PREFERRED CODE). NOTE: DO NOT USE WITHOUT MATERIALS & PROCESSES ENGINEERING APPROVAL.