APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A582	**LUSTERLESS BLACK URETHANE CLAD AND 1000, 3000, 5000, AND 6000 SERIES ALUMINUM AND ALUMINUM CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ALL SURFACES ONE COAT PER 201.
	C PAINT ALL SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 279 (OR 281).
	D TOUCH UP AS REQUIRED PER 285.
A583	**AMS-C-27725 FUEL TANK COATING AND LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME NON-FUEL SURFACES ONE COAT PER 202.
	D PAINT PRIMED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	E TOUCH UP AS REQUIRED PER 240 OR 285.
A584	**LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS (FOR CLOSE TOLERANCE FITS)**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME SPECIFIED SURFACES ONE COAT PER 202.
	C PAINT PRIMED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D TOUCH UP AS REQUIRED PER 285.
A585	**LUSTERLESS BLACK URETHANE AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT INTERIOR SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 235, 242, OR 285.
A586	**LUSTERLESS BLACK URETHANE AND 16NXXXX FINISH CLAD OR 1000, 3000, 5000, AND 6000 SERIES ALUMINUM ALLOYS OR ALUMINUM CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT INTERIOR SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 235, 242, OR 285.