APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A593	**WHITE URETHANE AND LUSTERLESS GRAY URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	E TOUCH-UP AS REQUIRED PER 237 OR 284.
A594	**LUSTERLESS GRAY URETHANE AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ALL SURFACES ONE COAT PER 201.
	C PAINT INTERIOR SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 242 OR 284.
A595	**LUSTERLESS GRAY URETHANE AND 16NXXXX FINISH CLAD & 1000,3000,5000, & 6000 SERIES ALUM. ALLOYS AND ALUMINUM CASTINGS (FOR CLOSE TOLERANCE FITS)**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT INTERIOR SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 242 OR 284.
A596	**WHITE URETHANE AND LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D PAINT REMAINING SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	E TOUCH UP AS REQUIRED PER 237 OR 285.
A597	**P6096-2 FLAT BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT ALL SURFACES WITH P6096-2 FLAT BLACK URETHANE COATING PER 266 (OR 286).
	D TOUCH UP AS REQUIRED PER 241.