APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A609	**GRAY URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS** A ANODIZE ALL SURFACES PER 111. B PRIME ONE COAT ALL SURFACES PER 201. C PAINT ALL SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 289 (OR 292). D TOUCH UP AS REQUIRED PER 291.
A610	**GRAY URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS** **(FOR CLOSE FIT TOLERANCES)** A ANODIZE ALL SURFACES PER 111. B PRIME ONE COAT SPECIFIED SURFACES PER 202. C PAINT PRIMED SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 290 (OR 292). D TOUCH UP AS REQUIRED PER 291.
A611	**REWORK OF ANODIZED PART - GRAY URETHANE AND 16NXXXX FINISH.** **ALL ALUMINUM ALLOYS** A CLEAN AND BRUSH CHEM FILM ALUMINUM SURFACES REQUIRING PRIMER PER 134. B PRIME ONE COAT SPECIFIED INTERIOR SURFACES PER 202. C PAINT SPECIFIED SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 290 (OR 292). D PRIME EXTERIOR EXPOSED SURFACES ONE COAT PER 202. E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSY PER DRAWING 16N0001. F TOUCH UP AS REQUIRED PER 242 AND 291.
A612	**GRAY URETHANE AND 16NXXXX FINISH** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS** A ANODIZE ALL SURFACES PER 111. B PRIME ALL SURFACES ONE COAT PER 201. C PAINT SPECIFIED SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 290 (OR 292). D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSY PER DRAWING 16N0001. E TOUCH UP AS REQUIRED PER 242 AND 291.
A613	**PRIMER AND GRAY URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS** A ANODIZE ALL SURFACES PER 111. B PRIME ONE COAT SURFACES SPECIFIED FOR GRAY COLOR PER 202. C PRIME TWO COATS REMAINING SURFACES PER 205 (OR 245). D PAINT SPECIFIED SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 290 (OR 292). E TOUCH UP AS REQUIRED PER 236 AND 291.