APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A623	**WHITE ACRYLIC LACQUER/WHITE URETHANE AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	D FINISH EXTERIOR EXPOSED SURFACE AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 235, 242 OR 295.
A624	**WHITE ACRYLIC LACQUER/WHITE URETHANE AND LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	D PAINT REMAINING SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	E TOUCH UP AS REQUIRED PER 295.
A625	**AMS-C-27725 FUEL TANK COATING AND WHITE ACRYLIC LACQUER/WHITE URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME REMAINING SURFACES ONE COAT PER 202.
	D PAINT REMAINING SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E TOUCH UP AS REQUIRED PER 240 OR 295.
A626	**PRIMER AND WHITE ACRYLIC LACQUER/WHITE URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SURFACES NOT REQUIRING WHITE COLOR PER 205 (OR 245).
	C PRIME ONE COAT SURFACES REQUIRING WHITE COLOR PER 202.
	D PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E TOUCH UP AS REQUIRED PER 236 OR 295.
A627	**WHITE ACRYLIC LACQUER/WHITE URETHANE AND 16NXXXX CLAD AND 1000, 3000, 5000 AND 6000 SERIES ALUMINUM ALLOYS AND CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ALL SURFACES ONE COAT PER 201.
	C PAINT INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	D FINISH EXTERIOR EXPOSED SURFACE AFTER ASSEMBLY PER DRAWING 16N0001.
	E TOUCH UP AS REQUIRED PER 235, 242 OR 295.