APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH

A716 **PRIMER, AMS-C-27725 FUEL TANK COATING, WHITE URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**

A ANODIZE ALL SURFACES PER 111.
B PRIME TWO COATS SPECIFIED INTERIOR AREAS PER 205 (OR 245).
C PRIME ONE COAT SURFACES SPECIFIED FOR WHITE COLOR PER 202.
D PAINT SPECIFIED AREAS WITH WHITE URETHANE COATING PER 222 (OR 274).
E APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL AREA PER 221.
F PRIME EXTERIOR EXPOSED SURFACES ONE COAT PER 202.
G FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
H TOUCH UP AS REQUIRED PER 235, 236, 237, 240, AND 242.

A717 **PRIMER, WHITE URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**

A ANODIZE ALL SURFACES PER 111.
B PRIME TWO COATS SPECIFIED INTERIOR SURFACE PER 205 (OR 245).
C PRIME ONE COAT SURFACES SPECIFIED FOR WHITE COLOR PER 202.
D PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
E PRIME EXTERIOR EXPOSED SURFACES ONE COAT PER 202.
F FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
G TOUCH UP AS REQUIRED PER 235, 236, 237 AND 242.

A720 **PRIMER AND DARK GRAY URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**

A ANODIZE ALL SURFACES PER 111.
B PRIME TWO COATS ON SPECIFIED SURFACES PER 205 (OR 245).
C PRIME ONE COAT ON SURFACES SPECIFIED FOR DARK GRAY COLOR PER 202.
D PAINT SPECIFIED SURFACES WITH DARK GRAY URETHANE COATING PER 257 (OR 277).
E TOUCH UP AS REQUIRED PER 236 AND 258.

A721 **DARK GRAY URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**

A ANODIZE ALL SURFACES PER 111.
B PRIME ONE COAT ALL SURFACES PER 201.
C PAINT ALL SURFACES WITH DARK GRAY URETHANE COATING PER 263 (OR 277).
D TOUCH UP AS REQUIRED PER 258.

A722 **PRIMER AND DARK GRAY URETHANE ALUMINUM ALLOY CASTINGS**

A CHEM FILM ALL SURFACES PER 105.
B PRIME TWO COATS ON SPECIFIED SURFACES PER 205 (OR 245).
C PRIME ONE COAT ON SURFACES SPECIFIED FOR DARK GRAY COLOR PER 202.
D PAINT SPECIFIED SURFACES WITH DARK GRAY URETHANE COATING PER 257 (OR 277).
E TOUCH UP AS REQUIRED PER 236 AND 258.