APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A753	**PRIMER, LUSTERLESS GRAY URETHANE, AND 16NXXXX FINISH ALUMINUM ALLOY CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205.
	C PRIME REMAINING SURFACES ONE COAT PER 202.
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE PER 282 (OR 280).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 236, 242, AND 284.
A754	**PRIMER, WHITE URETHANE, AND 16NXXXX FINISH ALUMINUM ALLOY CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205.
	C PRIME REMAINING SURFACES ONE COAT PER 202.
	D PAINT SPECIFIED SURFACES WITH WHITE URETHANE PER 222 (OR 274).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 236, 237, AND 242.
A755	**WHITE URETHANE, LUSTERLESS GRAY URETHANE, AND LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	E PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	F TOUCH UP AS REQUIRED PER 237, 284, AND 285.
A756	**WHITE ACRYLIC LACQUER/WHITE URETHANE, LUSTERLESS GRAY URETHANE, & 16NXXXX FINISH. CLAD,1000,3000 5000 & 6000 SERIES ALUM. ALLOYS & ALUM. CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED PRIMED SURFACES WITH LUSTERLESS GRAY URETHANE PER 282 (OR 280).
	D PAINT SPECIFIED PRIMED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 242, 284, AND 295.