APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A757	**PRIMER, AMS-C-27725 FUEL TANK COATING, AND WHITE ACRYLIC LACQUER/WHITE URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING TO SPECIFIED INTERIOR FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME TWO COATS ON SPECIFIED INTERIOR NON-FUEL AND NON-WHITE SURFACES PER 205 (OR 245).
	D PRIME ONE COAT ON SPECIFIED SURFACES REQUIRING WHITE COLOR PER 202.
	E PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	F TOUCH UP AS REQUIRED PER 236, 240, AND 295.
A758	**PRIMER, WHITE ACRYLIC LACQUER/WHITE URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SPECIFIED INTERIOR SURFACES PER 205 (OR 245)
	C PRIME ONE COAT SURFACES SPECIFIED FOR WHITE COLOR PER 202.
	D PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E PRIME EXTERIOR EXPOSED SURFACES ONE COAT PER 202.
	F FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	G TOUCH UP AS REQUIRED PER 235, 236, 242, AND 295.
A759	**WHITE ACRYLIC LACQUER/WHITE URETHANE, LUSTERLESS GRAY URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296)
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE PER 282 (OR 280).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 242, 284 AND 295.
A760	**AMS-C-27725 FUEL TANK COATING, WHITE ACRYLIC LACQUER/WHITE URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME ONE COAT REMAINING INTERIOR SURFACES PER 202.
	D PAINT SPECIFIED INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E PRIME ONE COAT EXTERIOR EXPOSED SURFACES PER 202.
	F FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	G TOUCH UP AS REQUIRED PER 235, 240, 242, AND 295.