APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A761	**PRIMER, WHITE ACRYLIC LACQUER/WHITE URETHANE, AND LUSTERLESS GRAY URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SURFACES SPECIFIED FOR PRIME PER 205 (OR 245).
	C PRIME THE REMAINING SURFACES PER 202.
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE PER 282 (OR 280).
	E PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	F TOUCH UP AS REQUIRED PER 236, 242, 284, AND 295.
A762	**WHITE ACRYLIC LACQUER/WHITE URETHANE, LUSTERLESS GRAY URETHANE, AND LUSTERLESS BLACK URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	E PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	F TOUCH UP AS REQUIRED PER 284, 285 AND 295.
A763	**PRIMER, WHITE URETHANE, AND 16NXXXX FINISH ALUMINUM ALLOY CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205 (OR 245).
	C PRIME REMAINING SURFACES ONE COAT PER 202.
	D PAINT SPECIFIED SURFACES WITH LIGHT GRAY TEFLON URETHANE COATING PER 261 (OR 287) FOR FSD AIRCRAFT (61: NO. 2 THRU NO. 6, 62: NO. 1 AND NO. 2). PRODUCTION AIRCRAFT SHALL USE THE COLOR OF TEFLON URETHANE COATING SPECIFIED ON THE APPLICABLE 16NXXXX AIRCRAFT PAINTING DRAWING.
	E PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	F FINISH REMAINING EXTERIOR SURFACES AFTER ASSEMBLY PER 16N0001.
	G TOUCH UP AS REQUIRED PER 235, 236, 237, 242, AND 262 (FOR THE GRAY COLOR ON FSD AIRCRAFT). TOUCH UP ON PRODUCTION AIRCRAFT PER 235, 236, 237, 242, AND 298.