APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH

A764 **PRIMER, WHITE URETHANE, AND 16NXXXX FINISH**
BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS

A ANODIZE ALL SURFACES PER 111.
B PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205 (OR 245).
C PRIME REMAINING SURFACES ONE COAT PER 202.
D PAINT SPECIFIED SURFACES WITH LIGHT GRAY TEFLON-URETHANE COATING PER 261 (OR 287) FOR FSD AIRCRAFT (61: NO. 2 THRU NO. 6, 62: NO. 1 AND NO. 2). PRODUCTION AIRCRAFT SHALL USE THE COLOR OF TEFLON-URETHANE COATING SPECIFIED ON THE APPLICABLE 16NXXXX AIRCRAFT PAINTING DRAWING.
E PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
F TOUCH UP AS REQUIRED PER 236, 237, AND 262 (FOR THE GRAY COLOR ON FSD AIRCRAFT). TOUCH UP ON PRODUCTION AIRCRAFT PER 236, 237, AND 298.

A765 **WHITE ACRYLIC LACQUER/WHITE URETHANE, LUSTERLESS BLACK URETHANE, AND 16NXXXX FINISH**
BARE 2000 OR 7000 SERIES ALUMINUM ALLOYS

A ANODIZE ALL SURFACES PER 111.
B PRIME ONE COAT ALL SURFACES PER 201.
C PAINT SPECIFIED INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
D PAINT SPECIFIED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
F TOUCH UP AS REQUIRED PER 235, 237 ,242, 285, AND 295.

A766 **WHITE URETHANE, WHITE ACRYLIC LACQUER/WHITE URETHANE, AND LUSTERLESS GRAY URETHANE**
BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS

A ANODIZE ALL SURFACES PER 111.
B PRIME ONE COAT ALL SURFACES PER 201.
C PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
D PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
E PAINT THE REMAINING SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
F TOUCH UP AS REQUIRED PER 237, 284, AND 295.

A767 **PRIMER, WHITE URETHANE, AND WHITE ACRYLIC LACQUER/WHITE URETHANE**
BARE 2000 OR 7000 SERIES ALUMINUM ALLOYS

A ANODIZE ALL SURFACES PER 111.
B PRIME ONE COAT SURFACES SPECIFIED FOR WHITE COLOR PER 202.
C PRIME TWO COATS SURFACES SPECIFIED FOR "PRIME" PER 205 (OR 245).
D PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
E PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
F TOUCH UP AS REQUIRED PER 236, 237 AND 295.