APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A768	**AMS-C-27725 COATING, WHITE URETHANE, WHITE ACRYLIC LACQUER/WHITE URETHANE & LUSTERLESS GRAY URETHANE. BARE 2000 OR 7000 SERIES ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME ONE COAT THE REMAINING SURFACES PER 202.
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	E PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	F PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	G TOUCH UP AS REQUIRED PER 237, 240, 284 AND 295.
A769	**PRIMER, WHITE ACRYLIC LACQUER/WHITE URETHANE, AND 16NXXXX FINISH. ALUMINUM ALLOY CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205 (OR 245).
	C PRIME REMAINING SURFACES ONE COAT PER 202.
	D PAINT SPECIFIED INTERIOR SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 236, 242, OR 295.
A770	**AMS-C-27725 FUEL TANK COATING, WHITE URETHANE, AND WHITE ACRYLIC LACQUER/WHITE URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY AMS-C-27725 COATING ON SPECIFIED FAYING SURFACES AND SURFACES EXPOSED TO FUEL PER 221.
	C PRIME ONE COAT REMAINING SURFACES PER 202.
	D PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	E PAINT REMAINING SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	F TOUCH UP AS REQUIRED PER 237, 240, OR 295.
A771	**PRIMER, DARK GRAY URETHANE, AND 16NXXXX FINISH ALUMINUM ALLOY CASTINGS - PYLON**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME TWO COATS SPECIFIED INTERIOR SURFACES PER 205 (OR 245).
	C PRIME ONE COAT REMAINING SPECIFIED SURFACES PER 202.
	D PAINT SPECIFIED INTERIOR SURFACES WITH DARK GRAY URETHANE COATING PER 257 (OR 277).
	E FINISH EXTERIOR SURFACES AFTER ASSEMBLY PER DRAWING 16N0005.
	F TOUCH UP AS REQUIRED PER 236, 242, 246 OR 258.