APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A776	**PRIMER, LUSTERLESS GRAY URETHANE, AND 16NXXXX FINISH BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SPECIFIED SURFACES PER 205 (OR 245).
	C PRIME ONE COAT REMAINING SURFACES PER 202.
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	F TOUCH UP AS REQUIRED PER 235, 236, 242, OR 284.
A777	**PRIMER, 16NXXXX FINISH, AND CHROMIUM PLATE 2000 AND 7000 SERIES ALUMINUM ALLOYS (DO NOT USE WITHOUT M&P ENGINEERING APPROVAL)**
	A CHROME PLATE SPECIFIED SURFACES PER 186.
	B BRUSH CHEM FILM REMAINING SURFACES PER 134.
	C PRIME TWO COATS SPECIFIED SURFACES PER 205.
	D PRIME ONE COAT REMAINING SURFACES PER 202.
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSY PER APPLICABLE 16NXXXX AIRCRAFT PAINTING DRAWING.
	F TOUCH-UP AS REQUIRED PER 235, 236, 242, OR 298.
A778	**WHITE URETHANE AND SOLID FILM LUBRICANT CLAD AND 1000, 3000, 5000, AND 6000 SERIES ALUMINUM ALLOYS**
	A CHEM FILM ALL SURFACES PER 105.
	B APPLY SOLID FILM LUBE TO SPECIFIED SURFACES PER 207 IN THICKNESSES OR DIMENSIONS AS NOTED.
	C PRIME ONE COAT REMAINING SURFACES PER 202.
	D PAINT PRIMED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	E TOUCH-UP AS REQUIRED PER 242 OR 237.
A779	**PRIMER, WHITE URETHANE, AND LUSTERLESS GRAY URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SPECIFIED SURFACES PER 205 (OR 245).
	C PRIME ONE COAT REMAINING SURFACES PER 202.
	D PAINT SPECIFIED SURFACES WITH LUSTERLESS GRAY URETHANE PER 282 (OR 280).
	E PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	F TOUCH-UP AS REQUIRED PER 236, 237, 242, OR 284.
A780	**PRIMER, DARK GRAY URETHANE, AND SOLID FILM LUBRICANT BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B APPLY SOLID FILM LUBE TO SURFACES SPECIFIED PER 207.
	C PRIME TWO COATS ON SPECIFIED SURFACES PER 205 (OR 245).
	D PRIME ONE COAT ON SURFACES SPECIFIED FOR DARK GRAY COLOR PER 202.
	E PAINT SPECIFIED SURFACES WITH DARK GRAY URETHANE COATING PER 257 (OR 277).
	F TOUCH UP AS REQUIRED PER 236 AND 258.