APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A786	**PRIMER AND WHITE URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS ALL SURFACES PER 204.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D TOUCH UP AS REQUIRED PER 236 AND 237.
A787	**PRIMER & LUSTERLESS BLACK URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME SPECIFIED SURFACES ONE COAT PER 202.
	C PAINT SPECIFIED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D PRIME REMAINING SURFACES TWO COATS, PER 205.
	E TOUCH UP AS REQUIRED PER 285 OR 236.
A788	**PRIMER & LUSTERLESS BLACK URETHANE** **CLAD AND 1000, 3000, 5000 AND 6000 SERIES ALUMINUM ALLOYS AND CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME SPECIFIED SURFACES ONE COAT PER 202.
	C PAINT SPECIFIED SURFACES WITH LUSTERLESS BLACK URETHANE COATING PER 283 (OR 281).
	D PRIME REMAINING SURFACES TWO COATS, PER 205.
	E TOUCH UP AS REQUIRED PER 285 OR 236.
A789	**P6096-2 FLAT BLACK URETHANE** **BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A NOTE: THIS CODE IS INACTIVE. THIS CODE IS A DUPLICATE OF A559; USE A559 FOR NEW DESIGNS.
	B ANODIZE ALL SURFACES PER 111.
	C PRIME SPECIFIED SURFACES ONE COAT PER 202.
	D PAINT PRIMED SURFACES WITH P6096-2 FLAT BLACK URETHANE PER 217 (OR 286).
	E TOUCH UP AS REQUIRED PER 241
A790	**PRIMER, 16NXXXX FINISH, AND HARD ANODIZE** **2000 OR 7000 SERIES ALLOYS**
	A HARD ANODIZE ALL SURFACES PER 113.
	B PRIME TWO COATS SPECIFIED SURFACES PER 205.
	C PRIME ONE COAT REMAINING SURFACES PER 202. (TWO COATS PER 205 IS OPTIONAL.)
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSY PER APPLICABLE 16NXXXX AIRCRAFT PAINTING DRAWING.
	E TOUCH UP AS REQUIRED PER 235, 236, 242, OR 298.