APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A791	**MEDIUM GRAY TEFLON-URETHANE AND 16NXXXX FINISH BARE 2000 OR 7000 SERIES ALLOYS**
	A ANODIZE PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIC SURFACES WITH 2 COATS TEFLON URETHANE, MEDIUM GRAY COLOR, PER 301.
	D FINISH EXTERIOR SURFACES AFTER ASSY PER DRAWING 16N0001.
	E TOUCH UP PER 235, 236, 242, OR 302.
A792	**WHITE TEFLON-URETHANE CLAD AND 1000, 3000, 5000, AND 6000 SERIES ALUMINUM ALLOYS AND ALUMINUM CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C APPLY WHITE TEFLON URETHANE COATING PER 352.
	D TOUCH UP AS REQUIRED PER 350.
A793	**DARK GRAY URETHANE. AL ALLOY CASTINGS & CLAD OR 1000, 3000, 5000 OR 6000 SERIES ALUM. ALLOYS AND ELECTRICAL BONDING ON 2000 & 7000 SERIES ALUM.**
	A CHEM FILM ALL SURFACES PER 176.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT PRIMED SURFACES WITH DARK GRAY URETHANE COATING PER 263 (OR 277).
	D TOUCH UP AS REQUIRED PER 258.
A794	**PRIMER AND MEDIUM GRAY TEFLON-URETHANE. CLAD OR 1000, 3000, 5000, 6000 SERIES ALUMINUM ALLOYS AND ALUMINUM CASTINGS.**
	A CHEM FILM ALL SURFACES PER 176.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C APPLY MEDIUM GRAY TEFLON URETHANE ON SPECIFIED SURFACES PER 354.
	D TOUCH UP AS REQUIRED PER 355.
A795	**PRIMER, DARK GRAY URETHANE, AND 16NXXXX FINISH. REWORK OF PREVIOUSLY ANODIZED PYLON PARTS. ALL ALUMINUM ALLOYS.**
	A CLEAN AND BRUSH CHEM FILM EXPOSED SURFACES PER 134.
	B PRIME TWO COATS SPECIFIED SURFACES PER 205.
	C PAINT SPECIFIED INTERIOR SURFACES WITH DARK GRAY URETHANE COATING PER 257 (OR 277).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0005.
	E TOUCH UP AS REQUIRED PER 236, 246, OR 258.
A796	**PRIMER AND WHITE URETHANE BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME TWO COATS SPECIFIED SURFACES PER 205.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D TOUCH UP AS REQUIRED PER 236 AND 237.