APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A897	**WHITE ACRYLIC LACQUER/WHITE URETHANE, LUSTERLESS GRAY URETHANE, AND IVD ALUMINUM OR CAD PLATE 2000 AND 7000 SERIES ALUM (SPECIAL ELEC BOND APPL)**
	A ANODIZE ALL SURFACES PER 111 EXCEPT THOSE SURFACES SPECIFIED FOR IVD ALUMINUM OR CADMIUM PLATE, OR SURFACES SPECIFIED FOR ELECTRICAL BONDING PER FPS-3024.
	B CLEAN SURFACES SPECIFIED FOR IVD ALUMINUM OR CAD PLATE PER FPS-3001 PARA. 3.1.1.(A). IVD ALUMINUM TREAT PER MIL-C-83488 TYPE II CL2 OR CADMUIM PLATE PER MIL-C-8837 TYPE II CL1 SPECIFIED SURFACES.
	C PRIME ONE COAT SURFACES SPECIFIED FOR WHITE ACRYLIC LACQUER/ WHITE URETHANE AND LUSTERLESS GRAY URETHANE PER 202.
	D PAINT SPECIFIED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E PAINT REMAINING PRIMED SURFACES WITH LUSTERLESS GRAY URETHANE COATING PER 282 (OR 280).
	F TOUCH UP AS REQUIRED PER 295 AND 284.
	G
	NOTE: DO NOT USE WITHOUT MATERIALS AND PROCESSES ENGINEERING APPROVAL.
A898	**WHITE ACRYLIC LACQUER/WHITE URETHANE AND IVD ALUM OR CAD PLATE (SPECIAL ELEC BONDING APPLICATION) BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111 EXCEPT THOSE SURFACES SPECIFIED FOR IVD ALUMINUM OR CADMIUM PLATE.
	B CLEAN SURFACES SPECIFIED FOR IVD ALUM OR CAD PLATE PER FPS-3001 PARA. 3.1.1(A). IVD ALUMINUM TREAT PER MIL-C-83488 TYPE II CL2 OR CADMIUM PLATE PER MIL-C-8837 TYPE II CL1. SPECIFIED SURFACES.
	C PRIME ONE COAT SPECIFIED SURFACES PER 202.
	D PAINT PRIMED SURFACES WITH EITHER WHITE ACRYLIC LACQUER OR WHITE URETHANE COATING PER 294 (OR 296).
	E TOUCH UP AS REQUIRED PER 295.
	F
	NOTE: DO NOT USE WITHOUT MATERIALS AND PROCESSES ENGINEERING APPROVAL.
A899	**PRIMER AND IVD ALUMINUM OR CADMIUM PLATE (SPECIAL ELECTRICAL BONDING APPLICATION) BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A CLEAN ALL SURFACES PER FPS-3001 PARA. 3.1.1(A).
	B IVD ALUMINUM TREAT PER MIL-C-83488 TYPE II CL2 OR CADMIUM PLATE PER MIL-C-8837 TYPE II CL1.
	C PRIME ALL SURFACES PER 205 EXCEPT THOSE SURFACES SPECIFIED FOR ELECTRICAL BONDING PER FPS-3024.
	D TOUCH UP AS REQUIRED PER 236.
	NOTE: DO NOT USE WITHOUT MATERIALS AND PROCESSES ENGINEERING APPROVAL.