APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A905	**PRIMER ON SPECIFIED SURFACES. TOPCOAT APPLIED AFTER ASSY (FOR FS-X/F-2 PARTS) 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ON SPECIFIED SURFACES PER 202.
	C TOUCH UP AS REQUIRED PER 242.
A906	**WHITE URETHANE ON SPECIFIED SURFACES (FOR FS-X/ F-2 PARTS). ALUMINUM CASTINGS AND 1000, 3000, 5000, AND 6000 SERIES AND CLAD ALUMINUM ALLOYS**
	A CHEMICAL FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE TOPCOAT PER 222.
	D TOUCH UP AS REQUIRED PER 237.
A907	**LIGHT GRAY URETHANE ON SPECIFIED SURFACES (FOR FS-X/F-2 PARTS) ALUM. CASTINGS AND 1000, 3000, 5000 AND 6000 SERIES AND CLAD ALUMINUM ALLOYS**
	A CHEMICAL FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ON SPECIFIED SURFACES PER 202.
	C PAINT PRIMED SURFACES WITH LIGHT GRAY URETHANE COATING PER 254 (OR 276).
	D TOUCH UP AS REQUIRED PER PER 255.
A908	**PRIMER WITHOUT TOPCOAT (FOR FS-X/F-2 USE) CLAD AND 1000, 3000, 5000, AND 6000 SERIES ALUM. ALLOYS AND ALUMINUM CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ALL SURFACES ONE COAT PER 201.
	C TOUCH UP AS REQUIRED PER 242.
A909	**WHITE URETHANE AND EXTERIOR SURFACE WITH NO TOP-COAT (USED ON FS-X/F-2 PARTS W/TOPCOAT APPLIED AFTER ASSY) BARE 2000 AND 7000 SERIES ALUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED INTERIOR SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D TOUCH UP AS REQUIRED PER 242 AND 237.