APPENDIX A. Finish Codes

SECTION A. ALUMINUM ALLOYS

CODE	APPLICABLE FINISH
A925	**PRIMER AND WHITE URETHANE 16NXXXX FINISH CLAD AND 1000, 3000, 5000, AND 6000 SERIES ALUMINUM ALLOY AND ALUMINUM ALLOY CASTINGS**
	A CHEM FILM ALL SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 OR 274.
	D PAINT SPECIFIED SURFACES WITH DARK GRAY URETHANE COATING PER 257 OR 277. PRODUCTION AIRCRAFT SHALL USE THE COLOR OF URETHANE COATING SPECIFIED ON APPLICABLE 16NXXXX AIRCRAFT PAINTING DRAWING.
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001.
	F TOUCH UP AS REQUIRED PER 237, 242 AND 258 AS APPLICABLE. TOUCH UP AS REQUIRED ON PRODUCTION AIRCRAFT PER 298.
A926	**PRIMER AND 16NXXXX FINISH FOR SPECIAL ELECTRICAL BONDING APPLICATIONS.**
	A CHEM FILM SPECIFIED SURFACES FOR ELECTRICAL BONDING PER 178.
	B ANODIZE ALL OTHER SURFACES PER 111.
	C PRIME TWO COATS ON INTERIOR SURFACE PER 205 (OR 245)
	D PRIME EXTERIOR EXPOSED SURFACES ONE COAT PER 202.
	E FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0001, EXCEPT ELECTRICAL BOND AREA.
	F TOUCH UP AS REQUIRED PER 235, 236, AND 242.
A927	**PRIMER, WHITE URETHANE, AND 16NXXXX FINISH FOR SPECIAL ELECTRICAL BONDING APPLICATIONS.**
	A CHEM FILM SPECIFIED SURFACES FOR ELECTRICAL BONDING PER 178.
	B ANODIZE ALL OTHER SURFACES PER 111.
	C PRIME SURFACES SPECIFIED FOR PRIME TWO COATS PER 205 (OR 245).
	D PRIME REMAINING SURFACES, EXCEPT ELECTRICAL BOND AREA ONE COAT PER 202.
	E PAINT SPECIFIED SURFACES PER 16NXXXX DRAWING.
	F PAINT SPEDIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	G TOUCH UP AS REQUIRED PER 236, 237 AND 298.
A928	**PRIMER AND 6069-2; REWORK OF DETAIL PART AT ASSEMBLY.**
	A REACTIVATE CHEM FILMED SURFACES PER 105.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT PRIMED SURFACES WITH P6096-2 FLAT BLACK URETHANE PER 217 (OR 286).
A929	**GRAY URETHANE AND 16NXXXX FINISH - PYLONS BARE 2000 AND 7000 SERIES ALUMINUM ALLOYS**
	A ANODIZE ALL SURFACES PER 111 OR 112.
	B PRIME ALL SURFACES WITH ONE COAT OF PRIMER PER 201.
	C PAINT SPECIFIED SURFACES WITH GRAY COLOR 36270 URETHANE COATING PER 290 (OR 292).
	D FINISH EXTERIOR EXPOSED SURFACES AFTER ASSEMBLY PER DRAWING 16N0005.
	E TOUCH UP AS REQUIRED PER 242 AND 291.