APPENDIX A. Finish Codes

SECTION S. CORROSION RESISTANT STEEL ALLOYS

CODE	APPLICABLE FINISH
S668	**DARK GRAY URETHANE FINISH OVER IVD ALUMINUM - PYLONS. 300 SERIES OR HEAT TREATABLE CRES.**
	A PASSIVATE ALL SURFACES PER 146.
	B IVD ALUMINUM TREAT ALL SURFACES PER 520.
	C PRIME ONE COAT ALL SURFACES PER 201.
	D PAINT PRIMED SURFACES WITH GRAY COLOR 26493 SEMIGLOSS URETHANE COATING PER 541 (OR 542).
	E TOUCHUP AS REQUIRED PER 555.
S701	**LIGHT GRAY URETHANE AND PRIMER (FOR FS-X PARTS) AISI 410 OR 17-4PH CASTING DETAILS OR PARTS PREVIOUSLY PASSIVATED.**
	A CLEAN PER 135.
	B PRIME SPECIFIED SURFACES WITH ONE COAT OF PRIMER PER 202.
	C PAINT SPECIFIED SURFACES WITH LIGHT GRAY URETHANE PER 254
	D TOUCH UP AS REQUIRED PER 321 OR 348.
S702	**WHITE URETHANE. 300 SERIES OR HEAT TREATABLE CRES, EXCEPT TUBING**
	A PASSIVATE PER 146.
	B PRIME ONE COAT ALL SURFACES EXCEPT HOLES PER 202.
	C PAINT PRIMED SURFACES WITH WHITE URETHANE COATING PER 222.
	D TOUCH UP AS REQUIRED PER 324.
S703	**PRIMER AND CORROSION PREVENTIVE COMPOUND. 300 SERIES AND HEAT TREATABLE CRES.**
	A PASSIVATE PER 146.
	B PRIME ONE COAT SPECIFIED SURFACES PER 202.
	C APPLY CORROSION PREVENTIVE COMPOUND TO NOTED AREA PER 250.
	D TOUCH UP AS REQUIRED PER 321.
S704	**WHITE URETHANE AND 16NXXXX FINISH. HEAT TREATABLE CRES (EXCEPT TUBING).**
	A PASSIVATE PER 147.
	B PRIME ONE COAT ALL SURFACES PER 201.
	C PAINT SPECIFIED SURFACES WITH WHITE URETHANE COATING PER 222 (OR 274).
	D FINISH EXTERIOR SURFACES PER THE APPLICABLE 16NXXXX AIRCRAFT
	E TOUCH UP AS REQUIRED PER 334.
S705	**FMS-3014 FORM 2 ADHESIVE PRIMER 300 SERIES OR HEAT TREATABLE CRES**
	A PASSIVATE PER 146.
	B APPLY FMS-3014 FORM 2 TO SPECIFIED SURFACES PER 403.
	C TOUCH UP AS REQUIRE PER 523 (OR 524 AS APPLICABLE)