APPENDIX B. Basic Elements

Basic Element	Basic Element Step(s)
255	RESTORE CORROSION PROTECTION FINISH TO EDGES OR SURFACES OF ALUMINUM PARTS TRIMMED AT ASSEMBLY, AND MANUFACTURED AND BUCKED HEADS OF ALUMINUM FASTENERS INSTALLED AT ASSEMBLY LEVEL. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA 3.1.1(A). BRUSH CHEMICAL FILM PER MIL-C-5541 AND TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 LIGHT GRAY URETHANE COATING, COLOR 36375. FINISH HOLES (INCLUDING COUNTERSINKS) DRILLED AFTER PAINTING FOR REMOVABLE FASTENERS WHICH DO NOT HAVE INSERTS IN ACCORDANCE WITH THIS BASIC ELEMENT OR WITH ELEMENT 236.
256	RESTORE CORROSION PROTECTION FINISH TO EDGES OR SURFACES OF PLASTIC PARTS TRIMMED OR ABRAIDED AT ASSEMBLY, AND MANUFACTURED AND BUCKED HEADS OF ALUMINUM FASTENERS INSTALLED AT ASSEMBLY LEVEL. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF WHITE URETHANE COATING, COLOR 17875 OR 17925, PER MIL-C-83286 OR MIL-C-85285.
257	APPLY TWO COATS OF MIL-C-83286 OR MIL-C-85285 URETHANE COATING, DARK GRAY, COLOR 36320, ON SPECIFIED SURFACES.
258	RESTORE CORROSION PROTECTION TO EDGES OR SURFACES OF ALUMINUM PARTS TRIMMED AT ASSEMBLY, AND MANUFACTURED AND BUCKED HEADS OF ALUMINUM FASTENERS INSTALLED AT ASSEMBLY LEVEL. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA 3.1.1(A). BRUSH CHEMICAL FILM PER MIL-C-5541 AND TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 DARK GRAY URETHANE COATING, COLOR 36320. FINISH HOLES (INCLUDING COUNTERSINKS) DRILLED AFTER PAINTING FOR REMOVABLE FASTENERS WHICH DO NOT HAVE INSERTS IN ACCORDANCE WITH THIS BASIC ELEMENT OR WITH ELEMENT 236.
259	APPLY TWO COATS OF FMS-1027, TYPE 5, TEFLON-URETHANE COATING DARK GRAY, COLOR 36320, ON SPECIFIED SURFACES PER FPS-0004.
260	RESTORE CORROSION PROTECTION TO EDGES OR SURFACES OF ALUMINUM PARTS TRIMMED AT ASSEMBLY, AND MANUFACTURED AND BUCKED HEADS OF ALUMINUM FASTENERS INSTALLED AT ASSEMBLY LEVEL. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.1(A). BRUSH CHEMICAL FILM PER MIL-C-5541 AND TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF FMS-1027, TYPE 5, TEFLON-URETHANE COATING DARK GRAY, COLOR 36320.