APPENDIX B. Basic Elements

Basic Element	Basic Element Step(s)
309	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF NON-CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.4. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582,OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C-83286 OR MIL-C-85285 URETHANE COATING, GRAY, COLOR 36231.
310	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF NON-CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.4. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582,OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C C-83286 OR MIL-C-85285 URETHANE COATING, BLACK, COLOR 37038.
311	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF NON-CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.4. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C-83286 OR MIL-C-85285 URETHANE COATING, BLACK OR ORANGE YELLOW, COLORS 37038 & 13538 (WHICHEVER WAS PREVIOUSLY APPLIED).
312	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF NON-CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.4. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582,OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 WHITE URETHANE COATING, COLOR 17875 OR 17925.
313	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF NON-CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES CLEAN PER FPS-3001, PARA. 3.1.4. TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582,OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 DARK GRAY URETHANE COATING, COLOR 36320.