APPENDIX B. Basic Elements

Basic Element	Basic Element Step(s)
324	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 WHITE URETHANE COATING, COLOR 17875 OR 17925.
325	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH AMS-C-27725, TYPE 1 OR 2, FUEL TANK COATING.
326	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A) AND TOUCH UP WITH FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 WHITE URETHANE COATING, COLOR 17875 OR 17925 OR TWO COATS OF URETHANE OR TEFLON-URETHANE COATING OF THE COLOR SPECIFIED ON THE APPLICABLE 16N0001 AIRCRAFT PAINTING DRAWING (WHICHEVER WAS PREVIOUSLY APPLIED).
327	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 DARK GRAY URETHANE COATING, COLOR 36320 (IF PREVIOUSLY APPLIED).
328	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C-83286 OR MIL-C-85285 URETHANE COATING, FLAT WHITE, COLOR 37875.