APPENDIX B. Basic Elements

Basic Element	Basic Element Step(s)
329	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF URETHANE OR TEFLON-URETHANE COATING OF THE COLOR SPECIFIED ON THE APPLICABLE 16NXXXX AIRCRAFT PAINTING DWG.
330	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF P6096-2 OPTICAL NON-REFLECTIVE BLACK COATING, COLOR 37038.
331	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C-83286 OR MIL-C-85285 URETHANE COATING, BLACK OR ORANGE-YELLOW, COLORS 37038 & 13538 (WHICHEVER WAS PREVIOUSLY APPLIED).
332	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-22750 EPOXY ENAMEL OR MIL-C-83286 OR MIL-C-85285 URETHANE COATING, ORANGE-YELLOW, COLOR 13538.
333	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 DARK GRAY URETHANE COATING, COLOR 36320.