# APPENDIX B. Basic Elements

| Basic Element | Basic Element Step(s) |
|---|---|
| **334** | RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF URETHANE OR TEFLON-URETHANE COATING OF THE COLOR SPECIFIED ON THE APPLICABLE 16N0001 AIRCRAFT PAINTING DWG (WHICHEVER WAS PREVIOUSLY APPLIED). |
| **335** | RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-83286 OR MIL-C-85285 LUSTER-LESS BLACK URETHANE COATING, COLOR 37038. |
| **336** | RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-83286 OR MIL-C-85285 LUSTER-LESS GRAY URETHANE COATING, COLOR 36231. |
| **337** | RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY ONE COAT OF MIL-C-83286 OR MIL-C-85285 LUSTER-LESS GRAY URETHANE COATING, COLOR 36231 (IF PREVIOUSLY APPLIED). |
| **338** | RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, MIL-PRF-85582, OR FMS-1058-1 PRIMER, FOLLOWED BY TWO COATS OF MIL-L-81352 WHITE ACRYLIC LACQUER OR MIL-C-83286 OR MIL-C-85285 WHITE URETHANE COATING, COLOR 17875 OR 17925, (WHICHEVER WAS PREVIOUSLY APPLIED). |