APPENDIX B. Basic Elements

Basic Element	Basic Element Step(s)
555	RESTORE CORROSION PROTECTION TO EDGES AND SURFACES (E.G., HOLES, COUNTERSINKS, SPOTFACES, ETC.) OF CORROSION RESISTANT STEEL ALLOYS THAT HAVE BEEN MACHINED AFTER INITIAL CORROSION PROTECTION HAS BEEN APPLIED. FOR PAINTED SURFACES, CLEAN PER FPS-3001, PARA. 3.1.3(A). TOUCH UP WITH ONE COAT OF FMS-3027, MIL-PRF-23377, OR MIL-PRF-85582 PRIMER, FOLLOWED BY TWO COATS OF MIL-C-83286 OR MIL-C-85285 LIGHT SEMIGLOSS GRAY URETHANE COATING, COLOR 26493.