CHANGE INDEX - REVISION C

Item	Paragraph No.	Change
		applicable to extrusion stock but is applicable to the extrusions supplied."
		Reason: Incorporate Amendment No. 4.
7	3.10.1	Revise to read: "When sampled and tested in accordance with paragraph 4.2.5, test specimens shall meet the minimum tensile properties at room temperature as specified in the paragraphs:
	3.10.1.1	For all product forms except sheet:

	Longitudinal	Transverse
Ultimate Tensile Strength -		
KSI	240 Max.	240 Max.
KSI	220 Min.	220 Min.
Yield Strength at 0.2% Offset -		
KSI	190	190
Elongation - Percent in 4D		
Up to 50 sq. in.	12	10
Over 50 to 200 sq. in.	12	8
Over 200 sq. in.	10	7
Plate 5/8" to 3/16" thick	10	8
Reduction of Area - Percent		
Up to 200 sq. in.	35	25
Over 200 sq. in.	30	20

3.10.1.2 for Sheet: (less than 3/16" thick)

Ultimate Tensile Strength -		
KSI	240 Max.	240 Max.
KSI	215 Min.	215 Min.