

# EcoMortar®

Ready mixed Natural Hydraulic Lime Mortar

## StrongStipple - R100

Ready-mix mortar for fine lime finishes



### Backgrounds

Most surfaces, including plasterboard and painted surfaces

### Natural colour

White

### Consumption

1.6 kg x m<sup>2</sup> x mm of thickness

### Packaging

25 kg bags

### Shelf life & guarantee

12 months in sealed original bag, stored in dry conditions.

### Application recommendations

Water addition: 5.5 to 6 litre per bag 25kg

Mix with a mortar whisk for maximum 5 minutes. On a clean, straight surface, apply a coat of maximum 5 mm. When different background materials meet, apply a mesh (of 10\*10mm) over the joint extending 150mm each side.

### Coloured fine finishes

Lime washes > Apply when sufficiently dry.

Fresco finishes > Apply when still fresh.

Fine finishes > All fine lime renders/plasters finishes are acceptable. *EcoMortar® Finish EF or TF* for steel float or sponge finishes is also acceptable.

Stucco/marmorino finishes > when dry, use *EcoMortar® Stucco* (0-0.04mm stucco type Saint-Astier® mortar, see relevant data sheet). This can be finished to a polish by qualified craftsmen.