



URAI PAINTS  
[www.urpaints.com](http://www.urpaints.com)

# ATM Synthetic Resin Alkyd Enamel

Bulletin no. ....

Description	A synthetic resin enamel, an ideal to apply on wood or metal substrates. Application is for both of interior and exterior. It provides long lasting protection against extreme weather condition change. Retention colour for long life.																																										
Application	Suitable to be using as top coat on wood or metal substrates such as handrail, grills for windows, curved steel, machines, etc.																																										
Technical Data	<table><tr><td>Product type</td><td>:</td><td colspan="2">Alkyd resin</td></tr><tr><td>Appearance</td><td>:</td><td colspan="2">Viscous liquid in various colour by follow to ATM Alkyd Enamel Catalog</td></tr><tr><td>Finish</td><td>:</td><td colspan="2">Matt &amp; Gloss</td></tr><tr><td>Specific Gravity (water = 1)</td><td>:</td><td colspan="2">0.9 – 1.0</td></tr><tr><td>Viscosity</td><td>:</td><td colspan="2">85 - 95 KU at 25 °C</td></tr><tr><td>Application tools</td><td>:</td><td colspan="2">Brush, roller or spray</td></tr><tr><td>Diluent</td><td>:</td><td colspan="2">Lobster Enamel Thinner no. T07</td></tr><tr><td>Drying time at 25 °C</td><td></td><td colspan="2"></td></tr><tr><td>- Dry to touch</td><td>:</td><td colspan="2">2 - 3 hours</td></tr><tr><td>- Dry to recoat</td><td>:</td><td colspan="2">16 - 24 hours.</td></tr></table>			Product type	:	Alkyd resin		Appearance	:	Viscous liquid in various colour by follow to ATM Alkyd Enamel Catalog		Finish	:	Matt & Gloss		Specific Gravity (water = 1)	:	0.9 – 1.0		Viscosity	:	85 - 95 KU at 25 °C		Application tools	:	Brush, roller or spray		Diluent	:	Lobster Enamel Thinner no. T07		Drying time at 25 °C				- Dry to touch	:	2 - 3 hours		- Dry to recoat	:	16 - 24 hours.	
Product type	:	Alkyd resin																																									
Appearance	:	Viscous liquid in various colour by follow to ATM Alkyd Enamel Catalog																																									
Finish	:	Matt & Gloss																																									
Specific Gravity (water = 1)	:	0.9 – 1.0																																									
Viscosity	:	85 - 95 KU at 25 °C																																									
Application tools	:	Brush, roller or spray																																									
Diluent	:	Lobster Enamel Thinner no. T07																																									
Drying time at 25 °C																																											
- Dry to touch	:	2 - 3 hours																																									
- Dry to recoat	:	16 - 24 hours.																																									
Painting System	<div>Surface preparation :</div> <p>Make sure the surface to be painted is free from dust, dirt, grease, waxy contaminant and loose particles. Rust or millscales should be removed.</p> <div>Coating System :</div> <p>Resinous Wood</p> <table><tr><td>●</td><td>Lobster Aluminium wood primer no. 1800</td><td>1 coat</td></tr><tr><td>●</td><td>ATM Undercoat White no. 1600</td><td>1 coat</td></tr><tr><td>●</td><td>ATM Synthetic Resin Alkyd Enamel</td><td>2 coat</td></tr></table> <p>Normal Hard Wood</p> <table><tr><td>●</td><td>ATM Undercoat White no. 1600</td><td>1 coat</td></tr><tr><td>●</td><td>ATM Synthetic Resin Gloss Enamel</td><td>2 coat</td></tr></table> <p>Steel or Metal Substrates</p> <table><tr><td>●</td><td>ATM Oxide Primer (Grey or red oxide)</td><td>1 coat</td></tr><tr><td>●</td><td>ATM Synthetic Resin Gloss Enamel</td><td>2 coat</td></tr></table>			●	Lobster Aluminium wood primer no. 1800	1 coat	●	ATM Undercoat White no. 1600	1 coat	●	ATM Synthetic Resin Alkyd Enamel	2 coat	●	ATM Undercoat White no. 1600	1 coat	●	ATM Synthetic Resin Gloss Enamel	2 coat	●	ATM Oxide Primer (Grey or red oxide)	1 coat	●	ATM Synthetic Resin Gloss Enamel	2 coat																			
●	Lobster Aluminium wood primer no. 1800	1 coat																																									
●	ATM Undercoat White no. 1600	1 coat																																									
●	ATM Synthetic Resin Alkyd Enamel	2 coat																																									
●	ATM Undercoat White no. 1600	1 coat																																									
●	ATM Synthetic Resin Gloss Enamel	2 coat																																									
●	ATM Oxide Primer (Grey or red oxide)	1 coat																																									
●	ATM Synthetic Resin Gloss Enamel	2 coat																																									
Coverage	8 - 12 sq.m/ litre /coat																																										

**DISCLAIMER:** The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.



URAI PAINTS  
[www.urpaints.com](http://www.urpaints.com)

# ATM Synthetic Resin Alkyd Enamel

Bulletin no. ....

Storage & Shelf life	Maximum 5 years in sealed container. Keep away from heat/ sparks/ open flames. No smoking. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.
Safety, Health and Environment Information	Keep out of reach of children. Use only outdoors or in a well-ventilated area. Wear protective gloves, eye and face protection. Avoid contact with skin or eyes. Wash thoroughly after handling. IF ON SKIN; Wash with plenty of soap and rinse skin with clean water. IF IN EYES, Rinse cautiously with water for several minutes. Do not empty into drains. Avoid release to the environment.
Packing	0.875 Litres, 3.5 Litres and 17.5 Litres.

**DISCLAIMER:** The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.