



URAI PAINTS
www.urpaints.com

ATM Wood Finish Paint

Bulletin no.

Description	A supreme wood finish paint which developed from special acrylic resin to give semi-gloss finish. High durable coating with excellent adhesion and flexibility. Water and UV resistant. Long lasting protection coating with free from lead and mercury compounds.																				
Application	Suitable to apply on wood piece, wood plank or fibre cement. Including to concrete or masonry. It can be applied to both of Interior and Exterior.																				
Technical Data	<table><tr><td>Product type</td><td>: Acrylic Emulsion</td></tr><tr><td>Appearance</td><td>: Colour viscous liquid regarding to catalog.</td></tr><tr><td>Film type</td><td>: Egg shell matt</td></tr><tr><td>Specific Gravity (water = 1)</td><td>: 1.10 – 1.15</td></tr><tr><td>Viscosity</td><td>: 100 – 105 KU at 25 °C</td></tr><tr><td>pH</td><td>: 8.5 – 9.5</td></tr><tr><td>Application tools</td><td>: Brush – Roller – Conventional spray</td></tr><tr><td>Drying time at 25 °C</td><td></td></tr><tr><td>- Dry to touch</td><td>: 30 minutes.</td></tr><tr><td>- Dry to recoat</td><td>: 1 – 2 hours.</td></tr></table>	Product type	: Acrylic Emulsion	Appearance	: Colour viscous liquid regarding to catalog.	Film type	: Egg shell matt	Specific Gravity (water = 1)	: 1.10 – 1.15	Viscosity	: 100 – 105 KU at 25 °C	pH	: 8.5 – 9.5	Application tools	: Brush – Roller – Conventional spray	Drying time at 25 °C		- Dry to touch	: 30 minutes.	- Dry to recoat	: 1 – 2 hours.
Product type	: Acrylic Emulsion																				
Appearance	: Colour viscous liquid regarding to catalog.																				
Film type	: Egg shell matt																				
Specific Gravity (water = 1)	: 1.10 – 1.15																				
Viscosity	: 100 – 105 KU at 25 °C																				
pH	: 8.5 – 9.5																				
Application tools	: Brush – Roller – Conventional spray																				
Drying time at 25 °C																					
- Dry to touch	: 30 minutes.																				
- Dry to recoat	: 1 – 2 hours.																				
Painting System	<p>The surface should be clean and dry. Free from dust, dirt, grease or loose particles. For new surface, leaves it to be full cured at least 1 month before apply top coating to avoid any damaging or colour fade out.</p> <table><tr><td>Wood surface</td><td>For resinous wood, priming with ATM Aluminium Wood Primer per 1 coat.</td></tr><tr><td>Wood plank or Fibre cement surface</td><td>No primer is required except the natural wood tone is desirable. Apply P-312 for primer before go to next step.</td></tr></table> <p>Top coat by ATM Wood Finish Paint for 2 coats.</p>	Wood surface	For resinous wood, priming with ATM Aluminium Wood Primer per 1 coat.	Wood plank or Fibre cement surface	No primer is required except the natural wood tone is desirable. Apply P-312 for primer before go to next step.																
Wood surface	For resinous wood, priming with ATM Aluminium Wood Primer per 1 coat.																				
Wood plank or Fibre cement surface	No primer is required except the natural wood tone is desirable. Apply P-312 for primer before go to next step.																				
Coverage	35 – 40 sq.m/ gallon. /coat																				
Storage & Shelf life	Maximum 5 years in sealed container. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.																				
Safety, Health and Environment Information	Keep out of reach of children. Use in a well-ventilated area. Avoid contact with skin or eyes. Wash thoroughly after handling. If on skin, wash with plenty of soap and rinse skin with clean water. If in eyes, rinse cautiously with water for several minutes. Do not use empty container for food stuff. Do not empty into drains.																				

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.



URAI PAINTS
www.urpaints.com

Technical Data Sheet

ATM Wood Finish Paint

Bulletin no.

Packing

0.946 Litres/ 3.785 Litres and 18.925 Litres.

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3) South Sathorn rd., Yannawaa, Sathorn, Bangkok 10120. Tel: +66 2 312 1049-50, +66 2 750 4808-9 Fax: +66 2 312 1163