



URAI PAINTS
www.urpaints.com

Technical Data Sheet

Lobster Synthetic Resin Alkyd Enamel

Bulletin no.

Description	A premium synthetic resin enamel, an ideal to apply on wood or metal. Application is for both of interior and exterior. It provides long lasting protection against extreme weather condition change. Retention colour for long life.																																
Application	Suitable to be using as top coat on wood or metal substrates such as handrail, grills for windows, curved steel, machines, etc.																																
Technical Data	<table><tr><td>Product type</td><td>:</td><td>Alkyd resin</td></tr><tr><td>Appearance</td><td>:</td><td>Viscous liquid in various colour by follow to Lobster Alkyd Enamel Catalog</td></tr><tr><td>Finish</td><td>:</td><td>Matt & Gloss</td></tr><tr><td>Specific Gravity (water = 1)</td><td>:</td><td>0.9 – 1.0</td></tr><tr><td>Viscosity</td><td>:</td><td>85 - 95 KU at 25 °C</td></tr><tr><td>Application tools</td><td>:</td><td>Brush, roller or spray</td></tr><tr><td>Diluent</td><td>:</td><td>Lobster Enamel Thinner no. T07 or Lion brand Turpentine Substitute AAA no. T21</td></tr><tr><td colspan="3">Drying time at 25 °C</td></tr><tr><td>- Dry to touch</td><td>:</td><td>2 - 3 hours</td></tr><tr><td>- Dry to recoat</td><td>:</td><td>16 - 24 hours.</td></tr></table>			Product type	:	Alkyd resin	Appearance	:	Viscous liquid in various colour by follow to Lobster Alkyd Enamel Catalog	Finish	:	Matt & Gloss	Specific Gravity (water = 1)	:	0.9 – 1.0	Viscosity	:	85 - 95 KU at 25 °C	Application tools	:	Brush, roller or spray	Diluent	:	Lobster Enamel Thinner no. T07 or Lion brand Turpentine Substitute AAA no. T21	Drying time at 25 °C			- Dry to touch	:	2 - 3 hours	- Dry to recoat	:	16 - 24 hours.
Product type	:	Alkyd resin																															
Appearance	:	Viscous liquid in various colour by follow to Lobster Alkyd Enamel Catalog																															
Finish	:	Matt & Gloss																															
Specific Gravity (water = 1)	:	0.9 – 1.0																															
Viscosity	:	85 - 95 KU at 25 °C																															
Application tools	:	Brush, roller or spray																															
Diluent	:	Lobster Enamel Thinner no. T07 or Lion brand Turpentine Substitute AAA no. T21																															
Drying time at 25 °C																																	
- Dry to touch	:	2 - 3 hours																															
- Dry to recoat	:	16 - 24 hours.																															
Painting System	<p>Surface preparation :</p> <p>Make sure the surface to be painted is free from dust, dirt, grease, waxy contaminant and loose particles. Rust or millscale should be removed.</p> <p>Coating System :</p> <p>Resinous Wood</p> <table><tr><td>● Lobster Aluminium wood primer</td><td>1 coat</td></tr><tr><td>● Lobster Undercoat White no. 1600</td><td>1 coat</td></tr><tr><td>● Lobster Synthetic Resin Alkyd Enamel</td><td>2 coat</td></tr></table> <p>Normal Hard Wood</p> <table><tr><td>● Lobster Undercoat White no. 1600</td><td>1 coat</td></tr><tr><td>● Lobster Synthetic Resin Alkyd Enamel</td><td>2 coat</td></tr></table> <p>Steel or Metal Substrates</p> <table><tr><td>● Lobster Grey or Red Oxide Primer</td><td>1 coat</td></tr><tr><td>● Lobster Synthetic Resin Alkyd Enamel</td><td>2 coat</td></tr></table>			● Lobster Aluminium wood primer	1 coat	● Lobster Undercoat White no. 1600	1 coat	● Lobster Synthetic Resin Alkyd Enamel	2 coat	● Lobster Undercoat White no. 1600	1 coat	● Lobster Synthetic Resin Alkyd Enamel	2 coat	● Lobster Grey or Red Oxide Primer	1 coat	● Lobster Synthetic Resin Alkyd Enamel	2 coat																
● Lobster Aluminium wood primer	1 coat																																
● Lobster Undercoat White no. 1600	1 coat																																
● Lobster Synthetic Resin Alkyd Enamel	2 coat																																
● Lobster Undercoat White no. 1600	1 coat																																
● Lobster Synthetic Resin Alkyd Enamel	2 coat																																
● Lobster Grey or Red Oxide Primer	1 coat																																
● Lobster Synthetic Resin Alkyd Enamel	2 coat																																
Coverage	8 - 12 sq.m/ litre /coat																																

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3) South Sathorn rd., Yannawaa, Sathorn, Bangkok 10120. Tel: +66 2 312 1049-50, +66 2 750 4808-9 Fax: +66 2 312 1163



URAI PAINTS
www.urpaints.com

Technical Data Sheet

Lobster Synthetic Resin Alkyd Enamel

Bulletin no.

Storage & Shelf life	Maximum 5 years in sealed container. Keep away from heat/ sparks/ open flames. No smoking. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.
Safety, Health and Environment Information	Keep out of reach of children. Use only outdoors or in a well-ventilated area. Wear protective gloves, eye and face protection. Avoid contact with skin or eyes. Wash thoroughly after handling. IF ON SKIN; Wash with plenty of soap and rinse skin with clean water. IF IN EYES, Rinse cautiously with water for several minutes. Do not empty into drains. Avoid release to the environment.
Packing	0.085 Litres, 0.280 Litres, 0.875 Litres, 3.5 Litres and 17.5 Litres.

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3) South Sathorn rd., Yannawaa, Sathorn, Bangkok 10120. Tel: +66 2 312 1049-50, +66 2 750 4808-9 Fax: +66 2 312 1163