



URAI PAINTS
www.urapaints.com

ATM Spray Acrylic Lacquer (Various colours for multi-purpose)

Bulletin no.

Description	ATM spray acrylic lacquer is specially formulated from high quality of acrylic resin and nitrocellulose. It provides an exceptional property; Quick drying. Easy to paint with aerosol to give a colourful and gloss finish. Excellent adhesion to every substrate.																																		
Application	A universal coating that can be applied to many kinds of substrates such as steel, plastic, wood, etc.																																		
Technical Data	<table><tr><td>Product type</td><td>:</td><td colspan="2">Nitrocellulose and Acrylic Lacquer Resin</td></tr><tr><td>Appearance</td><td>:</td><td colspan="2">Liquid spray regarding to catalog.</td></tr><tr><td>Film type</td><td>:</td><td colspan="2">Gloss / Matt</td></tr><tr><td>Viscosity</td><td>:</td><td colspan="2">12-14 sec at 25 °C (In liquid state)</td></tr><tr><td>Flash point</td><td>:</td><td colspan="2">-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))</td></tr><tr><td>Air vapour pressure</td><td>:</td><td colspan="2">4.5 – 5 kg/cm² at 30 °C</td></tr><tr><td>Drying time</td><td>:</td><td>- Dry to touch</td><td>15 minutes</td></tr><tr><td></td><td></td><td>- Dry to recoat</td><td>1 hours</td></tr></table>			Product type	:	Nitrocellulose and Acrylic Lacquer Resin		Appearance	:	Liquid spray regarding to catalog.		Film type	:	Gloss / Matt		Viscosity	:	12-14 sec at 25 °C (In liquid state)		Flash point	:	-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))		Air vapour pressure	:	4.5 – 5 kg/cm ² at 30 °C		Drying time	:	- Dry to touch	15 minutes			- Dry to recoat	1 hours
Product type	:	Nitrocellulose and Acrylic Lacquer Resin																																	
Appearance	:	Liquid spray regarding to catalog.																																	
Film type	:	Gloss / Matt																																	
Viscosity	:	12-14 sec at 25 °C (In liquid state)																																	
Flash point	:	-73 °C (Based on the lowest flash point material, spray propellant (LPG – Liquefied Petroleum Gas))																																	
Air vapour pressure	:	4.5 – 5 kg/cm ² at 30 °C																																	
Drying time	:	- Dry to touch	15 minutes																																
		- Dry to recoat	1 hours																																
Application Instruction	<ul style="list-style-type: none">● Clean surface thoroughly to be free from rust, dirt and grease.● Shake can thoroughly 2 minutes before using and shake periodically during spray.● Spray from a distance of about 1 foot.● For better result apply several thin coatings with an interval of 10 minutes.● After spraying turn can upside down and press spray head to clean the spray nozzle.																																		
Coverage	Not available																																		

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3)
South Sathorn rd., Yannawa, Sathorn,
Bangkok 10120.
Tel: +66 2 312 1049-50, +66 2 750 4808-9
Fax: +66 2 312 1163
www.urapaints.com



URAI PAINTS
www.uraipaints.com

ATM Spray Acrylic Lacquer (Various colours for multi-purpose)

Bulletin no.

Storage & Shelf life	Maximum 3 years in sealed container. Protect from sunlight. Do not expose to temperatures exceeding 25-30 °C. Keep it in well-ventilated place.
Safety, Health and Environment Information	<ul style="list-style-type: none">● Keep out of reach of children.● Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.● Use in a well-ventilated area.● Do not spray on an open flame or other ignition source.● If on skin, wash with plenty of soap and rinse skin with clean water.● If in eyes, rinse cautiously with water for several minutes.● Do not pierce or burn, even after use.● Avoid release to the environment.
Packing	270 g

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Sales office: 52, 54 Soi Sathorn 11 (Sect. 3)
South Sathorn rd., Yannawa, Sathorn,
Bangkok 10120.
Tel: +66 2 312 1049-50, +66 2 750 4808-9
Fax: +66 2 312 1163
www.uraipaints.com